Z. CHEN, Z. GUAN, M. LI, Q. YANG, C. LI* (DALIAN INSTITUTE OF CHEMICAL PHYSICS, P. R. OF CHINA)

Enhancement of the Performance of a Platinum Nanocatalyst Confined within Carbon Nanotubes for Asymmetric Hydrogenation

Angew. Chem. Int. Ed. 2011, 50, 4913–4917.

A Platinum Nanocatalyst Confined within Carbon Nanotubes

Significance: A Pt nanocatalyst confined within nanochannels of carbon nanotubes (CNTs) was described. Treatment of multi-wall CNTs with 68 wt% HNO_3 (140 $^\circ\text{C}$, 14 h) gave the CNTs with open ends. After ultrasonication of the CNTs and H_2PtCl_6 in H_2O for 3 h, the mixture was stirred at r.t. for 48 h, and then heated to 110 $^\circ\text{C}$ with a heat range of 1 $^\circ\text{C}/\text{min}$ and held at 110 $^\circ\text{C}$ for 24 h. Reduction of the catalyst precursor with sodium formate led to Pt nanoparticles within the channel of CNTs, which were modified with cinchonidine in AcOH. Asymmetric hydrogenation of α -keto esters was performed under H_2 using the chirally modified catalyst affording the corresponding α -hydroxy esters with 86–96% ee.

SYNFACTS Contributors: Yasuhiro Uozumi, Yoichi M. A. Yamada, Maki Minakawa
Synfacts 2011, 8, 0913–0913 Published online: 20.07.2011
DOI: 10.1055/s-0030-1260706; Reg-No.: Y07011SF

Comment: Pt nanoparticles encapsulated within the nanochannel of CNTs [Pt/CNTs(in)] were characterized by TEM, HRTEM (high-resolution transmission electron microscopy), N_2 chemisorption, and CO chemisorption. Pt nanoparticles located on the outer surface of CNTs [Pt/CNTs(out)], Pt/AC (active carbon), and Pt/ Al_2O_3 showed lower catalytic activity under similar conditions. Pt/CNTs(in) were recovered by centrifugation (or filtration), and re-modified by cinchonidine in AcOH. The Pt/CNTs(in) catalyst was reused nine times without significant loss of catalytic activity (1st: 99.9% conversion, 96.4% ee; 10th: 99.9% conversion, 95.7% ee).

Category

Polymer-Supported Synthesis

Key words

carbon nanotubes

platinum

cinchonidine

asymmetric hydrogenation

SYNFACTS
of the month