Y. M. A. YAMADA,* S. M. SARKAR, Y. UOZUMI* (RIKEN ADVANCED SCIENCE INSTITUTE, WAKO, INSTITUTE FOR MOLECULAR SCIENCE AND THE GRADUATE SCHOOL FOR ADVANCED STUDIES, OKAZAKI, JAPAN)
Self-Assembled Poly(imidazole-palladium): Highly Active, Reusable Catalyst at Parts per Million to Parts per Billion Levels
J. Am. Chem. Soc. **2012**, *134*, 3190–3198.

Polymeric Imidazole Pd Catalyst for Cross-Couplings

Preparation of an imidazole palladium catalyst (MEPI-Pd **3**):

Allylic arylation–alkenylation of allylic acetates/carbonates:

The Suzuki–Miyaura coupling:

Significance: A self-assembled polymeric palladium catalyst MEPI-Pd **3** was prepared via the molecular convolution of (NH₄)₂PdCl₄ and poly[(N-vinylimidazole)-co-(N-isopropylacrylamide)]₅. MEPI-Pd **3** (0.8–40 mol ppm Pd) promoted the allylic arylation/alkenylation of allylic esters **4** with aryl/alkenylboron reagents **5** in water and/or alcohol to give the corresponding products **6**. MEPI-Pd **3** (0.28 mol ppm–0.1 mol% Pd) drove the Suzuki–Miyaura coupling of a variety of aryl chlorides, bromides, and iodides in water to give the corresponding biaryls **7**.

SYNFACTS Contributors: Yasuhiro Uozumi, Yoichi M. A. Yamada, Shaheen M. Sarkar
Synfacts 2012, 8(5), 0569 Published online: 18.04.2012
DOI: 10.1055/s-0031-1290933; Reg-No.: Y03912SF

Comment: MEPI-Pd **3** was reused without loss of catalytic activity for the allylic arylation and the Suzuki–Miyaura coupling. MEPI-Pd with 0.28 mol ppm Pd efficiently promoted the Suzuki–Miyaura coupling of iodotoluene and phenylboronic acid to afford **7b** quantitatively with a TON of 3,570,000 and a TOF of 119,000 h^{−1}. The authors reported a preliminary communication for the allylic arylation of allylic acetates (*Angew. Chem. Int. Ed.* **2011**, *50*, 9437; *Synfacts* **2011**, 1380).

Category

Polymer-Supported Synthesis

Key words

allylic arylation

amphiphilic imidazole polymers

heterogeneous palladium catalysis

Suzuki–Miyaura coupling

SYNFACTS
of the month