T.-L. CUI, W.-Y. KE, W.-B. ZHANG, H.-H. WANG, X.-H. LI,* J.-S. CHEN* (SHANGHAI JIAO TONG UNIVERSITY, P. R. OF CHINA)
Encapsulating Palladium Nanoparticles inside Mesoporous MFI Zeolite Nanocrystals for Shape-Selective Catalysis
Angew. Chem. Int. Ed. **2016**, 55, 9178–9182.

Shape-Selective Mesoporous Silicalite-Encapsulated Palladium Catalyst

Category

Polymer-Supported Synthesis

Key words

palladium catalysis

nanoparticles

zeolite catalysis

shape-selective catalysis

oxidation

hydrogenation

Synfact
of the month

Significance: Palladium nanoparticles encapsulated in mesoporous silicalite-1 (Pd@S1; pore size $5.3 \times 5.6 \text{ \AA}$, 1.7 wt% Pd) were prepared for use as a shape-selective catalyst. Reduction of nitrobenzene (**1a**) by NaBH_4 , oxidation of benzyl alcohol (**3a**) under O_2 , and the Suzuki–Miyaura coupling of iodobenzene (**5a**) with 4-methoxyphenylboronic acid proceeded in the presence of Pd@S1 to give the corresponding products **2a**, **4a**, and **6a** in 93–94% yield. Under similar conditions, the reactions of substrates with larger molecular size (**1b**, **3b**, and **5b**) gave the corresponding products in less than 4% yield.

Comment: The selectivity of the catalysis was evaluated by using Pd/C as catalyst as a control instead of Pd@S1 under similar conditions. Reduction of **1a**, **1b**, the oxidation of **3a**, **3b**, and the Suzuki–Miyaura coupling of **5a**, **5b** with 4-methoxyphenylboronic acid proceeded in the presence of Pd/C to give the corresponding products **2a**, **2b**, **4a**, **4b**, and **6a**, **6b** in 55–99% yield. In the coupling reaction of **5a** with 4-methoxyphenylboronic acid, Pd@S1 was reused fourteen times without significant loss of its catalytic activity.

SYNFACTS Contributors: Yasuhiro Uozumi, Takuma Sato, Aya Ohno
Synfacts 2016, 12(11), 1207 Published online: 18.10.2016
DOI: 10.1055/s-0036-1589340; Reg-No.: Y14116SF