Evaluation of the Occluding Characteristics of Nanosized Eggshell/Titanium Dioxide with or without Saliva

Stanley Chibuzor Onwubu¹ Phumlani Selby Mdluli² Shenuka Singh³ Vishal Bharuth⁴
Mokgadi Ursula Makgobole⁵

¹Department of Dental Sciences, Durban University of Technology (DUT), Durban, South Africa

²Department of Chemistry, Durban University of Technology (DUT), Durban, South Africa

³Discipline of Dentistry, University of KwaZulu-Natal (UKZN), Westville, South Africa

⁴Microscopy and Microanalysis Unit, University of KwaZulu-Natal (UKZN), Westville, South Africa

⁵Department of Chiropractic and Somatology, Durban University of Technology (DUT), Durban, South Africa

Address for correspondence Stanley Chibuzor Onwubu, MSc, Dental Sciences Department, Dental Technology Program, Durban University of Technology (DUT), Durban, South Africa (e-mail: 21445599@dut4life.ac.za).

Eur J Dent 2019;13:547–555

Abstract

Objectives The study reports on the effectiveness of a ball-milled nanosized titanium dioxide composite (EB@TiO₂) for DH management in comparison with commercial desensitizing paste with and without saliva.

Materials and Methods Forty-nine dentine specimens were prepared from extracted bovine anterior teeth. Twenty-one of the specimens were brushed with three desensitizing toothpaste for 7 days, namely: Group 1; EB@TiO₂, Group 2; Colgate Pro-relief; and Group 3; Sensodyne repair ($n = 7$). Twenty-four specimens were brushed with the toothpaste for 7 days and stored in artificial saliva (control) after brushing. Each specimen was subsequently posttreated in citric acid solution to test its stability in acidic condition. Field scanning electron microscope was used to evaluate the effectiveness of the dentine tubules occlusion. The biocompatibility of the composite was tested using BHK21 cell line.

Statistical Analysis One-way analysis of variance was used to analyze the percentage occluded area ratio values for all specimens ($\alpha = 0.05$). Independent t -test was further used to evaluate the occlusion differences with saliva and without saliva.

Results and Conclusions The number of dentine tubules decreased significantly after 7 days of brushing. Overall, the occlusion observe for EB@TiO₂ were significantly better than for Colgate Pro-relief and Sensodyne repair ($p < 0.05$). BHK21 assay suggested that composite had no significant effect on the BHK21 cell line. This study demonstrated that the composite effectively occluded open dentine tubules within 7 days of brushing.

Keywords

- dentine hypersensitivity
- desensitizing paste
- remineralization

Introduction

Globalization has created a rapid change in the diets and lifestyles of millions of people worldwide. In South Africa

for example, the reintroduction of the country to the global economy postapartheid in 1994 has witnessed the proliferation of foreign goods and a rapidly changing food environment.¹ Concerning, and in the context of oral health care,

this change has brought about the increase in consumption of energy drinks, and acidic beverages; which is reportedly linked to the incidence of dental diseases, such as dental caries and erosion of the enamel surface.^{2,3} More worrisome is that the excessive demineralization of the tooth surface due to erosion has been reported to initiate the onset of dentine hypersensitivity (DH).⁴⁻⁶

According to the Canadian Advisory Board on DH,⁷ DH is characterized by distinctive short, sharp pain arising from exposed dentinal tubules particularly in response to external stimuli that are typically thermal, evaporative, tactile, electrical, osmotic, or chemical changes which cannot be ascribed to any other form of dental defects or pathology. As reported in the literature, DH is one of the most clinically encountered problems in dentistry affecting between 10 to 30% of people worldwide.⁸ Although there have been conflicting reports on the exact prevalence of DH, nevertheless, the most common age range in which DH is frequently experienced is given as 20 to 50 years, with female patients predominantly affected.^{9,10} Moreover, and as Schiff et al¹¹ points out, DH has a negative consequence on the quality of life for dental patient as they are less compliant with oral hygiene recommendation; thus posing a challenge for oral health care providers to manage.

Many theories have been reportedly proposed to explain the mechanism of DH. However, the hydrodynamic theory expanded upon by Brannstrom is now accepted by the dental community as the most likely mechanism for DH occurrence.¹² In an attempt to control this process, products or agents that typically aimed to reduce fluid flow, and or interfere with the nerve impulses have been reported in the literature.^{11,13} At the first line of at-home therapy for DH management, the use of occluding agents is often recommended for effective treatment.¹⁴

Several different occluding agents such as potassium oxalates,¹⁵ sodium fluoride and sodium monofluorophosphate,¹² strontium salt,¹⁶ amorphous calcium phosphate containing casein phosphopeptide,¹⁷ and calcium glycerophosphate¹⁸ have been widely utilized in desensitizing paste for their dentine tubule occluding capabilities. Still, the effectiveness of the aforementioned occluding agents will depend on the flow of saliva. Moreover, due to the chemical composition of saliva, it can play a critical role in naturally reducing DH.^{13,19} Kleinberg¹⁹ revealed that saliva could reduce DH by depositing phosphate and calcium ions in the exposed tubules which ultimately result into the ions forming a protective layer on the surface of the tubules. In some patients; however, particularly those with conditions of hyposalivation and xerostomia, the flow of saliva is limited; which could further increase the risks of caries and tooth demineralization, thereby exacerbating DH.²⁰

In an attempt to address the above concern, Kleinberg in 2012 at the State University of New York-Stony Brook, patented novel occluding agents based on the understanding of the role that saliva plays in naturally reducing DH. This new technology comprises arginine (an amino acid with a pH 6.5–7.5), bicarbonate, pH buffer, and calcium carbonate.¹⁹ The said technology is marketing under the brand name

Colgate Pro-Argin.¹¹ It is reported that Pro-Argin technology function by occluding dentinal tubules using arginine to bind to the negatively charged dentin surface, which subsequently attracts a calcium-rich layer from the saliva to infiltrate and block the dentinal tubules.²⁰ However, its effectiveness in a highly acidic environment has been reported to be ineffective,²¹ thus leading to the reopening of the dentine tubules. Given the above drawbacks, a new occluding material consisting of an eggshell modified titanium dioxide composite recently proposed in DH management.²²

Importantly, studies^{23,24} have projected that the future of tooth remineralization will be the use of eggshell owing to its high bioavailability of calcium. Likewise, the use of titanium dioxide, particularly in nano form, and their combination with other abrasive agents have been proposed in the literature to occlude open dentine tubules.²⁵ In a recent report, the authors demonstrated that eggshell modified with titanium dioxide (EB@TiO₂) significantly improved the composite acidic resistant to erosive acids.²⁶ This present study, therefore, aimed to evaluate EB@TiO₂ occluding characteristic against commercially available toothpaste containing Pro-Argin (Colgate Pro-relief) and NovaMin (Sensodyne repair) with and without saliva in reducing DH. The formulated hypothesis tested was: EB@TiO₂ significantly occlude the open dentine tubules with or without saliva.

Materials and Methods

Two commercially available toothpastes namely: Sensodyne repair (GlaxoSmithKline, United Kingdom) and Colgate Pro-relief (Colgate-Palmolive, Poland) were used as the test desensitizing paste. Titanium dioxide (Anatase form) and citric acid were purchased from Sigma-Aldrich (Germany), and Merck (South Africa), respectively.

Eggshell-Titanium Dioxide Composite Preparation

Eggshell and titanium dioxide composite was prepared in accordance with the method reported in literature.²² An extensive details of the surface morphology, particle sizes, and phase of the prepared EB@TiO₂ can be found in other reported papers.^{22,27,28}

Preparation of Artificial Saliva

Artificial saliva was prepared following the method reported by Saporeti et al²⁹ with a slight modification. As specified in ►Table 1, the listed chemicals were prepared in 1L of volumetric flask using deionized water. The pH of the prepared saliva was given as 6.5.

Forty-nine anterior teeth extracted from bovine were collected from an abattoir, South Africa. Disinfecting and cleaning of the teeth followed by immersing in 10% chlorox-ylenol solution. With the aid of a diamond saw operating at a minimal speed, and cooled with water, the teeth were sectioned below the enamel-dentinal to prepare a dentine specimen having a dimension of 5 mm × 5 mm × 1 mm. A silicon carbide paper with particle size of 600 grits were further used to wet ground the specimens for 60 seconds. Thereafter, the specimens were embedded in a resin (AMT composite,

Table 1 Composition of the prepared artificial saliva (mg/L)

Chemicals	Concentration (mg/L)	Mass (g)
NaH ₂ PO ₃ H ₂ O	780	0.078
NaCl	500	0.05
KCl	500	0.05
CaCl ₂ H ₂ O	795	0.0795
NaS ₉ H ₂ O	5	0.0005
(NH ₄) ₂ SO ₄	300	0.03
Citric Acid	5	0.0005
NaHCO ₃	100	0.01
Urea	1000	0.1

Note: Preparation of dentine tooth specimens.

South Africa). The specimens were then soaked in a solution containing 4% wt. citric acid for 2 minutes to open up the tubules. As described in ►Table 2, the specimens were randomly assigned in different experimental groups.

Each specimen from the respective groups were brushed twice daily (morning and evening) with a toothbrush powered with 1.5v alkaline battery (Oralwise, China) for 1 minute and allowed to dry for 30 seconds before rinsing with deionized water. Brushing was performed at room temperature using 100 mg of respective toothpaste. The slurry of EB@TiO₂ was prepared by mixing 100 mg of the powder/200 µL of deionized water. After each brushing protocol, the specimens were immersed in saliva or without saliva as described in ►Table 2. At the end of the 7-day brushing, the treated specimens were exposed to 4% wt. citric acid solution for 2 minutes to determine the resistance to acidic challenge, and subsequently rinsed in deionized before blot drying.

Field Scanning Electron Microscope (FESEM; Carl Zeiss) was used to examine the treated specimens after each day of brushing from each respective group. The instrument was

operated in controlled environment and scan at 20 kV. Prior to FESEM observation, the specimens were dehydrated, sputter coated with electric conductive gold film. Using the captured image of 1500 magnification, a software (ImageJ; National Institute of Health, United States, <http://imagej.nih.gov/ij>) was used to compute the occluded tubules ratios by dividing the area of the occluded tubules by the total tubules area ($n = 7$). The % occluded area ratio were counted and used for statistical evaluation.

Biocompatibility Test

A cytotoxicity assay was performed on the prepared EB@TiO₂ to evaluate its biocompatibility. Before culturing, the sample was dispersed in a solvent (Dimethyl Sulfoxide). The BHK21 hamster kidney cells were grown in the laboratory following the process of culturing normal tissues.²² The cell viability were then evaluated using MTS assay. Auranofin was used as a negative control. All analyses were tested in duplicate and performed across two plates ($n = 6$).

Statistical Analysis

One-way analysis of variance (ANOVA) was used to analyze the mean occluded area ratio within the different groups, followed by a Bonferroni test ($\alpha = 0.05$). In addition, the independent *t*-test was used to compare the mean occluded area ratio observe for the specimens treated with saliva and without saliva ($\alpha = 0.05$). All analysis was performed using statistical software (IBM SPSS Statistics v24; IBM Corp.).

Results

Dentine Specimens Treated in 7 Days (without Saliva)

►Table 3 depicts the results of the dentine specimens measured in 7 days without saliva immersion. The total mean % ratio of the tubules occluded area for the dentine specimens

Table 2 The distribution of specimens according to the experimental group

Sample groups	Treatment condition		Brushing days	Total
	Without saliva	With saliva		
Artificial saliva	–	7	Twice daily (for 7 days)	7
EB@TiO ₂	7	7		14
Colgate Pro-relief	7	7		14
Sensodyne repair	7	7		14
Total	21	28		49

Note: Surface examination of the treated specimens. EB@TiO₂, eggshell-titanium dioxide.

Table 3 ANOVA test comparison of the occluded area (without saliva)

Treatment group	N	Mean ± SD	Standard error	95% confidence interval		p-Value	Posthoc Bonferroni's test
				Lower bound	Upper bound		p-Value
EB@TiO ₂	7	64.7 ± 1.3	0.655	63.318	66.070	0.000	0.028 ^{1,2}
Colgate Pro-relief	7	62.0 ± 3.2	0.655	60.624	63.376		0.000 ^{1,3}
Sensodyne repair	7	22.7 ± 4.8	0.655	21.358	24.111		0.000 ^{2,3}

Abbreviation: SD, standard deviation.

Note: Superscript numbers indicate significant differences between the sample groups (ANOVA, $p < 0.05$). EB@TiO₂, eggshell-titanium dioxide.

treated with EB@TiO₂, Colgate Pro-relief, and Sensodyne repair was statistically different ($p < 0.001$).

Notably, and after 7 days of brushing, the EB@TiO₂ group had the highest % mean occluded area ($64.7 \pm 1.3\%$), while the Sensodyne repair treated group had the lowest % mean occluded area ($22.7 \pm 4.8\%$). The Bonferroni's correction results are given in ►Table 3. The % tubules occluded for the test group (EB@TiO₂) were statistically higher when compared against the Colgate Pro-relief group ($p < 0.05$), and the Sensodyne repair group ($p < 0.001$). Equally, the % occluded area measured for the Colgate Pro-relief was significantly higher than that observed for Sensodyne repair ($p < 0.001$). ►Fig. 1 illustrates the differences in the % tubules occluded per day with the three desensitizing paste materials (EB@TiO₂, Colgate Pro-relief, and Sensodyne).

The Paired sample test, mean, and standard deviation results for the dentine specimen's pre- and postacidic challenge are given in ►Table 4. There was no significant different found in the EB@TiO₂ group pre- and postacidic treatment ($p > 0.05$). In contrast, both the Colgate Pro-relief and Sensodyne repair treated group showed differences ($p < 0.001$).

The FESEM image of the occluded dentine tubules for dentine specimens treated without storing in artificial saliva after 7 days brushing test is reflected in ►Fig. 2. In day 1 (►Fig. 2B1), day 2 (►Fig. 2B2), the group treated with Colgate Pro-relief showed more evidence of tubule occlusion when compared against the group treated with EB@TiO₂ and Sensodyne repair. However, the EB@TiO₂ group showed a better evidence of tubule remineralization in day 3 (►Fig. 2A3) and day 4 (►Fig. 2A4). Similarly, there was a

Fig. 1 Differences in mean tubules occluded of dentine specimens treated with EB@TiO₂, Colgate Pro-relief, and Sensodyne repair desensitizing paste materials after 2 minutes of brushing without saliva immersion (7-day brushing test [$n = 7$]). EB@TiO₂, eggshell-titanium dioxide.

complete remineralization or sealing of the tubules in the EB@TiO₂ group in day 5 (►Fig. 2A5), day 6 (►Fig. 2A6), and day 7 (►Fig. 2A7).

The posttreatment in citric acid solution (4 wt.%) of the specimens are shown in ►Fig. 2 (A–C8). Nonetheless, the specimen treated EB@TiO₂ (►Fig. 2A8) showed superior acid resistance with no visible differences pre- and postacidic challenge when compared against the specimens treated with Colgate Pro-relief (►Fig. 2B8) and Sensodyne repair (►Fig. 2C8), respectively.

Dentine Specimens Treated in 7 Days (with Saliva)

The mean, standard error, standard deviation, and ANOVA results for the dentine specimens stored in artificial saliva after brushing treatment are shown in ►Table 5. The total mean % ratio of the tubules occluded area for the dentine specimens stored in artificial saliva alone, treated with EB@TiO₂, Colgate Pro-relief, and Sensodyne repair was statistically different ($p < 0.001$).

It was found that the % occluded mean measured for the EB@TiO₂ group was the highest ($72.0 \pm 1.0\%$), while the specimens stored in artificial saliva alone without treatment had the lowest % mean occluded area ($7.3 \pm 2.3\%$). The Bonferroni's correction results are shown in ►Table 5. The EB@TiO₂ group mean % occluded area was statistically better when compared against the Colgate Pro-relief, and the Sensodyne repair ($p < 0.001$). More so, the % occluded area measured for the Sensodyne repair was significantly higher than that observed for Colgate Pro-relief ($p < 0.001$). All the treatment groups showed a significant improvement in occluding the tubules when compared against the samples stored in artificial saliva alone (< 0.001). ►Fig. 3 illustrates the differences in the % tubules occluded per day with the three desensitizing paste materials (EB@TiO₂, Colgate Pro-relief, and Sensodyne) and artificial saliva.

►Table 6 provides the paired sample test, mean, and standard deviation results for the dentine specimen's (stored in artificial saliva) pre- and postacidic challenge. No difference was found in the Sensodyne repair group pre- and postacidic treatment ($p > 0.05$). By contrast, there was a significant difference observed for the EB@TiO₂, Colgate Pro-relief, and specimens stored in artificial saliva alone ($p < 0.001$).

The FESEM images of the dentine specimens treated with EB@TiO₂, Colgate Pro-relief, and Sensodyne repair for 7 days and storing in artificial saliva are shown in ►Fig. 4. The observed images indicate the occlusion of EB@TiO₂ groups (A1–A7) were different from other test groups (Artificial saliva, Colgate Pro-relief, and Sensodyne repair). ►Fig. 4 (A–D8)

Table 4 Paired sample test comparison of occluded area ratio pre- and postacidic treatment

Treatment group	Occluded area (%)		<i>p</i> -Value
	Preacidic challenge (mean $\pm$ SD)	Postacidic challenge (mean $\pm$ SD)	
EB@TiO ₂	97.9 $\pm$ 1.3	97.1 $\pm$ 1.2	0.318
Colgate Pro-relief	88.9 $\pm$ 3.2	33.9 $\pm$ 4.1	0.000
Sensodyne repair	71.3 $\pm$ 4.9	9.3 $\pm$ 2.4	0.000

Abbreviation: SD, standard deviation.

Fig. 2 Representative FESEM micrograph for the dentine surface after brushing for 7 days without saliva immersion using (A) EB@TiO₂; (B) Colgate Pro-relief; (C) Sensodyne repair (1–7 represents number of each day of brushing with the respective desensitizing paste, and 8 represent post acidic exposure). FESEM, field scanning electron microscope. EB@TiO₂, eggshell-titanium dioxide.

Table 5 ANOVA test Comparison of the occluded area (samples stored in artificial saliva)

Treatment group	N	Mean ± SD	Standard error	95% confidence interval		p-Value	Posthoc Bonferroni test
				Lower bound	Upper bound		p-Value
Artificial saliva		7.3 ± 2.3	0.636	5.953	8.578	0.000	0.000 ¹⁻⁵
EB@TiO ₂		72.0 ± 1.0	0.636	70.708	73.333		0.000 ^{2,3}
Colgate Pro-relief		34.3 ± 8.6	0.636	33.034	35.659		0.000 ^{3,4}
Sensodyne repair		50.3 ± 3.0	0.636	49.014	51.639		0.000 ^{2,4}

Abbreviation: SD, standard deviation.

Note: Superscript numbers indicate significant differences between the sample groups (ANOVA, $p < 0.001$). EB@TiO₂, eggshell-titanium dioxide.

Fig. 3 Differences in mean tubules occluded of dentine specimens treated with EB@TiO₂ Colgate Pro-relief, and Sensodyne repair desensitizing paste materials after 2 minutes of brushing and immersed in saliva (7 day brushing test [$n = 7$]). EB@TiO₂, eggshell-titanium dioxide.

revealed dissimilarity posttreatment of the specimens in citric acid solution (4 wt.%). The occluded tubules remain intact after acidic challenge for both the EB@TiO₂ and Sensodyne treated group. On the contrary, the tubules in the Colgate Pro-relief (► Fig. 4C8) treated specimens were visibly reopened postacidic challenge.

Biocompatibility Testing

The biocompatibility of EB@TiO₂ with the BHK21 cell line is shown in ►Fig. 5. In comparison to the negative control, the EB@TiO₂ appear to show little effect on the BHK21 cell lines. However, there was 56% cell viability at 100 µg/mL.

Discussion

Over the last decade, DH has been extensively researched owing to its widespread prevalence and noticeable painful oral health problem affecting many individuals.³⁰ The main aim of the paper to evaluate the effectiveness of a modified

Table 6 Paired sample test comparison of occluded area ratio pre- and postacidic treatment (samples stored in artificial saliva)

Treatment Group	Occluded area (%)		p-Value
	Preacidic challenge (mean ± SD)	Postacidic challenge (mean ± SD)	
Artificial saliva	10.9 ± 2.3	5.7 ± 1.8	0.001
EB@TiO ₂	99.3 ± 1.0	85.0 ± 3.8	0.000
Colgate Pro-relief	80.1 ± 8.6	9.0 ± 2.2	0.000
Sensodyne repair	90.4 ± 3.0	88.1 ± 3.9	0.245

Abbreviation: SD, standard deviation.

Fig. 4 Representative FESEM micrograph for the dentine surface after brushing for seven days with saliva immersion using (A) Artificial saliva; (B) EB@TiO₂; (C) Colgate Pro-relief; (D) Sensodyne repair (1–7 represents with the respective desensitizing paste, and 8 post acidic exposure). FESEM, field scanning electron microscope. EB@TiO₂, eggshell-titanium dioxide.

Fig. 5 Percentage cell viability.

nanosized eggshell powder titanium dioxide composite (EB@TiO₂) in reducing DH. The composite was prepared through the mechanochemical activation method. Importantly, this method utilizes a mechanical energy to create structural changes as well as stimulate chemical reactions.³¹ Consequently, it becomes possible to cause structural changes and particle size reduction in the EB@TiO₂ composite.^{27,28} Conversely, the effectiveness of the prepared EB@TiO₂ in reducing DH was compared against Colgate Pro-relief and Sensodyne with or without immersion saliva. As suggested in the literature,^{32–37} their occluding capabilities were evaluated

using the bovine model. The morphological changes pre- and postacidic treatment of the specimens were evaluated with FESEM. The EB@TiO₂ treated specimens showed good tubule occlusion that still remain effective in acidic condition for both samples treated with and without saliva. This leads to the acceptance of the study hypothesis.

With respect to time, in the specimens treated without saliva, Colgate Pro-relief showed instant occluding of the dentine tubules. This is consistent with clinical studies^{38,39} that Pro-Argin technology provides instant relief of DH. According to the mechanism proposed by Kleinberg,¹⁹ it may be assumed that dentine with a negative charge surface attracts the positive charge arginine constituent of the Colgate Pro-relief which subsequently causes the adherence of calcium carbonate to the dentin surface. This in turn promotes the occlusion of the tubules. Despite this, the overall dentine tubule occlusion observed in the samples treated with EB@TiO₂ were significantly better than Colgate Pro-relief ($p < 0.05$) and Sensodyne repair ($p < 0.001$), respectively. These differences could be attributed to the modification of the carbonate structure in eggshell with titanium dioxide.²² According to Cutler,²⁵ nanosized titanium dioxide, together with abrasive materials facilitate the occluding of dentine tubules, thus contributing to reducing of DH. Added to this, the nanosized calcium carbonate materials have unique high surface energy—thus facilitating the attachment of calcium-rich ions on the oral tooth surface.⁴⁰

Furthermore, the occlusion measured for Sensodyne repair was statistically lower compared against the Colgate Pro-relief ($p < 0.001$). At the end of 7 days brushing, EB@TiO₂ had the highest occluded area ($97.8 \pm 1.3\%$) followed by Colgate Pro-relief ($88.9 \pm 3.2\%$), and lastly Sensodyne repair ($71.3 \pm 4.9\%$). Overall, the highest (64.7 ± 1.3) occlusion measured was in the EB@TiO₂ group, while Sensodyne repair had the lowest (22.7 ± 4.8 ; ►Table 3). This difference may be related to the constituent of the various test materials. Although studies^{41,42} have shown that calcium sodium phosphosilicate (NovaMin) constituent of the Sensodyne repair could obstruct dentine tubules to some extent, Yu et al⁴³ however, argued that the Ca²⁺ and PO₄ are protected by glass particles which need to be trapped for the Ca²⁺ and PO₄ to be localized. The consequence of this is that there might be a delay in the action of the NovaMin to effectively promote the closing of dentine tubules.⁴³ Since the brushing test was performed in 7 days, without saliva, the inferior occluding characteristics observed for Sensodyne repair could be attributed to the absence of saliva to trap the Ca²⁺ and PO₄³⁻.

On the other hand, for the specimens treated with saliva immersion, all the tested material demonstrated a significant occlusion difference when compared with the those found in saliva alone ($p < 0.001$). While saliva is reported to facilitate remineralization by the deposition of calcium and phosphate,^{13,19} the finding from this study suggests that the occlusion of specimens in saliva alone without desensitizing paste treatment were highly inferior (►Table 5). This may, however, be attributed to the treatment duration (►Table 2). As reported in literature,¹² the occluding capabilities of saliva occur gradually within a long time. In support of the role saliva plays in reducing DH, the dentine tubules occlusion observed for Sensodyne repair showed an outstanding occlusion when compared against the samples treated without saliva. Similar significant occluding abilities were measured for EB@TiO₂ treated with saliva immersion ($p < 0.05$).

Contrary to the above, the dentine tubules occlusion observed for the samples treated with Colgate Pro-relief with saliva treatment were consistently inferior at each day of brushing to those measured for the samples treated without saliva ($p < 0.001$; ►Table 6). In contrast, other studies^{11,38} claimed that the interaction of calcium carbonate and arginine encourages endogenous calcium and phosphate ions to deposit and occlude the dentin tubules. However, Yang et al⁴⁴ found that Colgate Pro-relief showed no significant changes after treatment and immersion in artificial saliva for 14 days. The above author findings corroborate with the same observation found in this study.

Moreover, the stability of occluding agents, particularly in a high acidic oral environment, is an important criterion for evaluating the efficiency of desensitizing paste in occluding dentine tubules.⁴⁵ This is more important as the oral cavity is often bombarded with citric acid that is highly common in the soft drinks and fruit juices found in our daily diets. In light of these, the effectiveness of the dentine occlusion observed with the different desensitizing paste was assessed

posttreatment in a solution containing 4wt.% citric acid. The results observed for Colgate Pro-relief suggests that the product demonstrated an acid resistant to a certain extent. This can further be supported by the FESEM images that visibly showed that some of the closed dentine tubules were reopened after exposure to the citric acid solution (►Fig. 2B8, and 4C8). This; however, could be attributed to the solubility of calcium phosphates in an acidic environment.²¹

In terms of the Sensodyne repair, the acid resistance effectiveness measured exhibit different behavior in the samples treated with and without saliva. In the group treated without saliva, nearly all the tubules were reopened after the exposure to citric acid (►Fig. 2C8). Similar findings were observed by Yu et al⁴³ where the deposits created by NovaMin on the dentine surface were almost completely removed by the citric acid solution. In contrast, the samples treated with saliva (►Fig. 4D8), the Sensodyne repair demonstrated an outstanding acidic resistance characteristic ($p > 0.05$). The difference observed for both sample treatments may be associated with the role the saliva plays. It can, therefore, assume that the occlusion for the samples treated with Sensodyne and immersed in saliva had depth and penetration, thereby contributing to its acidic resistance.

As for the EB@TiO₂ group, the acidic resistant properties observed for the samples treated without saliva, pre- and postcitric acid exposure were comparable ($p > 0.05$). However, slight differences were observed for the samples treated and immersed in saliva. It was found that after citric exposure, some of the obstructing tubules were reopened (►Fig. 4B8). This notwithstanding, the FESEM images visibly validate that the acid resistant characteristics of EB@TiO₂ were superior to that of Colgate Pro-relief and to some extent Sensodyne repair. Consistent with Tao et al,⁴⁶ the stability of EB@TiO₂ in an acidic condition may have been influenced by the modification of eggshell with titanium dioxide. Further clinical research is; however, needed to substantiate the efficiency of EB@TiO₂ as biocomposite material for the management of DH.

Conclusion

In conclusion, and within the study limitation, the study established that the EB@TiO₂ composite successfully occludes open dentine tubules with and without saliva. It was also established that EB@TiO₂ achieved effectiveness after 3 days of brushing. The composites also provide outstanding acid resistant stability. Despite this, and given the size of the sample used for the study, larger and longer duration of treatment would be required to conclusively determine the efficiency of EB@TiO₂ in reducing DH.

Funding

The financial support provided by the National Research Foundation of South Africa (No. 104824) is acknowledged by the authors.

Conflict of Interest

None declared.

References

- Igumbor EU, Sanders D, Puoane TR, et al. "Big food," the consumer food environment, health, and the policy response in South Africa. *PLoS Med* 2012;9(7):e1001253
- Pinto SC, Bandeca MC, Silva CN, Cavassim R, Borges AH, Sampaio JE. Erosive potential of energy drinks on the dentine surface. *BMC Res Notes* 2013;6:67
- Giacaman RA, Pailahual V, Díaz-Garrido N. Cariogenicity induced by commercial carbonated beverages in an experimental biofilm-caries model. *Eur J Dent* 2018;12(1):27–35
- Salahi S, Ghanbari M, Moosaali F. Effect of Three Common Desensitizers in Reduction of the Dentin Hypersensitivity after Periodontal Surgery. *J Dent Biomater*. 2016;3:169–176.
- Rahardjo A, Nasia AA, Adiatman M, Maharani D. Efficacy of a toothpaste containing 5% potassium nitrate in desensitizing dentin hypersensitivity. *Asian J Pharm Clin Res*. 2016;9:345–347.
- Mafla AC, Lopez-Moncayo LF. Dentine sensitivity risk factors: a case-control study. *Eur J Dent* 2016;10(1):1–6
- Canadian Advisory Board on Dentin Hypersensitivity. Consensus-based recommendations for the diagnosis and management of dentin hypersensitivity. *J Can Dent Assoc* 2003;69(4):221–226
- Clark D, Levin L. Non-surgical management of tooth hypersensitivity. *Int Dent J* 2016;66(5):249–256
- Miglani S, Aggarwal V, Ahuja B. Dentin hypersensitivity: recent trends in management. *J Conserv Dent* 2010;13(4):218–224
- Colak H, Demirel S, Hamidi M, Uzgur R, Köseoğlu S. Prevalence of dentine hypersensitivity among adult patients attending a dental hospital clinic in Turkey. *West Indian Med J* 2012;61(2):174–179
- Schiff T, Delgado E, Zhang YP, Cummins D, DeVizio W, Mateo LR. Clinical evaluation of the efficacy of an in-office desensitizing paste containing 8% arginine and calcium carbonate in providing instant and lasting relief of dentin hypersensitivity. *Am J Dent* 2009;22 Spec No A:8A–15A
- Merh A, Singhbhal K, Parikh V, Mehta S, Kulkarni G. Comparative evaluation of immediate efficacy of diode laser versus desensitizing paste containing 8% arginine and calcium carbonate in treatment of dentine hypersensitivity: an in vivo study. *J Evol Med Dent Sci*. 2015;4(25):4346–4355
- Panagakos F, Schiff T, Guignon A. Dentin hypersensitivity: effective treatment with an in-office desensitizing paste containing 8% arginine and calcium carbonate. *Am J Dent* 2009;22 Spec No A:3A–7A
- Yang ZY, Wang F, Lu K, Li YH, Zhou Z. Arginine-containing desensitizing toothpaste for the treatment of dentin hypersensitivity: a meta-analysis. *Clin Cosmet Investig Dent* 2016;8:1–14
- Cunha-Cruz J, Stout JR, Heaton LJ, Wataha JC; Northwest PRECEDENT. Dentin hypersensitivity and oxalates: a systematic review. *J Dent Res* 2011;90(3):304–310
- Saeki K, Marshall GW, Gansky SA, Parkinson CR, Marshall SJ. Strontium effects on root dentin tubule occlusion and nano-mechanical properties. *Dent Mater* 2016;32(2):240–251
- Babu KG, Subramaniam P, Teleti S. Remineralization potential of varnish containing casein phosphopeptides-amorphous calcium phosphate with fluoride and varnish containing only fluoride: a comparative study. *Saudi J Oral Sci*. 2018;5(1):35
- Zalite V, Locs J. Characterization and Preparation of Calcium Phosphate Model Toothpaste for Tooth Enamel Remineralization. *Key Eng Mater* 2017;721:231:218
- Kleinberg I. SensiStat. A new saliva-based composition for simple and effective treatment of dentinal sensitivity pain. *Dent Today* 2002;21(12):42–47
- Strassler HE, Serio FG. Dentinal hypersensitivity: Etiology, Diagnosis And Management. *The Academy of Dental Therapeutics and Stomatology*; 2009:2–7
- Arnold WH, Prange M, Naumova EA. Effectiveness of various toothpastes on dentine tubule occlusion. *J Dent* 2015;43(4):440–449
- Onwubu SC, Mdluli PS, Singh S, Tlapana T. A novel application of nano eggshell/titanium dioxide composite on occluding dentine tubules: an in vitro study. *Braz Oral Res* 2019;33:e016
- Macri DV. Implementing a minimally invasive approach. *Dimens Dent Hyg* 2016;14:32–37
- Haghgoo R, Mehran M, Ahmadvand M, Ahmadvand MJ. Remineralization effect of eggshell versus nano-hydroxyapatite on caries-like lesions in permanent teeth (in vitro) *J Int Oral Health* 2016;8:435:439.
- Cutler ET. Prevention and treatment of oral diseases. In: Patent U, ed. USA: Squigle, Inc; 2014
- Onwubu SC, Mdluli PS, Singh S, Nyembe S, Thakur R. An in situ evaluation of the protective effect of nano eggshell/titanium dioxide against erosive acids. *Int J Dent* 2018. doi: 10.1155/2018/4216415
- Onwubu SC, Mdluli PS, Singh S. Evaluating the buffering and acid-resistant properties of eggshell-titanium dioxide composite against erosive acids. *J Appl Biomater Funct Mater* 2019;17(1):2280800018809914
- Onwubu SC, Mdluli PS, Singh S, Lawrence M, Ngombane Y. Characterization and in vitro evaluation of an acid resistant nanosized dental eggshell-titanium dioxide material. *Adv Powder Technol* 2019;30(4):766–773
- Saporeti MP, Mazzeiro ET, Sales WF. In vitro corrosion of metallic orthodontic brackets: influence of artificial saliva with and without fluorides. *Dental Press J Orthod* 2012;17(6):24e1–24e7
- Cunha-Cruz J, Wataha JC, Heaton LJ, et al. Northwest Practice-based Research Collaborative in Evidence-based DENTistry. The prevalence of dentin hypersensitivity in general dental practices in the northwest United States. *J Am Dent Assoc* 2013;144(3):288–296
- Hua Z, Nie M, Liu X, Wang Q. A clean strategy to prepare polylactide/hydroxyapatite bionanocomposites via solid mechanochemistry. *J Macromol Sci, Part B*. 2017;56(5):306–314
- Fonseca RB, Haiter-Neto F, Fernandes-Neto AJ, Barbosa GAS, Soares CJ. Radiodensity of enamel and dentin of human, bovine and swine teeth. *Arch Oral Biol* 2004;49(11):919–922
- Tanaka JLO, Medici Filho E, Salgado JAP, et al. Comparative analysis of human and bovine teeth: radiographic density. *Braz Oral Res* 2008;22(4):346–351
- Yassen GH, Platt JA, Hara AT. Bovine teeth as substitute for human teeth in dental research: a review of literature. *J Oral Sci* 2011;53(3):273–282
- Silva BG, Nunes Gouveia TH, Pereira da Silva MA, Bovi Ambrosano GM, Baggio Aguiar FH, Leite Lima DAN. Evaluation of home bleaching gel modified by different thickeners on the physical properties of enamel: an *in situ* study. *Eur J Dent* 2018;12(4):523–527
- Vajrabhaya LO, Korsuwannawong S, Harnirattisai C, Teinchai C. Changes in the permeability and morphology of dentine surfaces after brushing with a Thai herbal toothpaste: a preliminary study. *Eur J Dent* 2016;10(2):239–244
- Carvalho AO, Ayres AP, de Almeida LCAG, Briso ALF, Rueggeberg FA, Giannini M. Effect of peroxide bleaching on the biaxial flexural strength and modulus of bovine dentin. *Eur J Dent* 2015;9(2):246–250
- Ayad F, Ayad N, Zhang YP, DeVizio W, Cummins D, Mateo LR. Comparing the efficacy in reducing dentin hypersensitivity of

- a new toothpaste containing 8.0% arginine, calcium carbonate, and 1450 ppm fluoride to a commercial sensitive toothpaste containing 2% potassium ion: an eight-week clinical study on Canadian adults. *J Clin Dent* 2009;20(1):10–16
- 39 Docimo R, Montesani L, Maturo P, et al. Comparing the efficacy in reducing dentin hypersensitivity of a new toothpaste containing 8.0% arginine, calcium carbonate, and 1450 ppm fluoride to a commercial sensitive toothpaste containing 2% potassium ion: an eight-week clinical study in Rome, Italy. *J Clin Dent* 2009;20(1):17–22
 - 40 Nakashima S, Yoshie M, Sano H, Bahar A. Effect of a test dentifrice containing nano-sized calcium carbonate on remineralization of enamel lesions in vitro. *J Oral Sci* 2009;51(1):69–77
 - 41 Chiang YC, Chen HJ, Liu HC, et al. A novel mesoporous biomaterial for treating dentin hypersensitivity. *J Dent Res* 2010;89(3):236–240
 - 42 Yang H, Pei D, Chen Z, Lei J, Zhou L, Huang C. Effects of the application sequence of calcium-containing desensitising pastes during etch-and-rinse adhesive restoration. *J Dent* 2014;42(9):1115–1123
 - 43 Yu J, Yang H, Li K, Lei J, Zhou L, Huang C. A novel application of nanohydroxyapatite/mesoporous silica biocomposite on treating dentin hypersensitivity: an in vitro study. *J Dent* 2016;50:21–29
 - 44 Yang JC, Hu HT, Lee SY, et al. In vitro evaluation of dentin tubule occlusion for novel calcium lactate phosphate (CLP) paste. *Materials (Basel)* 2017;10(3):228
 - 45 Wang Z, Sa Y, Sauro S, et al. Effect of desensitising toothpastes on dentinal tubule occlusion: a dentine permeability measurement and SEM in vitro study. *J Dent* 2010;38(5):400–410
 - 46 Tao H, He Y, Zhao X. Preparation and characterization of calcium carbonate–titanium dioxide core–shell (CaCO₃@ TiO₂) nanoparticles and application in the papermaking industry. *Powder Technol* 2015;283:308–314