Effect of resealing on microleakage of resin composite restorations in relationship to margin design and composite type

Sibel A. Antonson¹

A. Ruya Yazici²

Zeynep Okte³

Patricia Villalta⁴

Donald E. Antonson¹

Patrick C. Hardigan⁵

ABSTRACT

Objective: To determine the relationship between margin preparation design and resin-composite type on microleakage with or without re-application of surface-penetrating sealant.

Methods: Class-I resin-composite restorations were completed for 128 extracted human molars. Half of the margins were beveled, the other half, butt-joint. Half of each group was restored with Filtek-Supreme (FS), the other half with Esthet-X (EX) using their respective adhesive systems. Margins were etched and sealed with a surface-penetrating sealant, Fortify. The samples were stored in water 24h, and thermocycled (5,000 cycles, 5°C-55°C). Then, samples were abraded using a toothbrush machine (6,000 strokes). Half of the restorations from each sealant group (n=16) were resealed, and the other half had no further treatment. Thermocycling and tooth brushing were repeated. The samples were sealed with nail polish, immersed in methylene-blue for 8h, sectioned, and magnified digital photographs were taken. Three examiners assessed dye penetration. A 2x2x2 multi-layered Chi-Square analysis, using Cochran-Mantel-Haenszel test was conducted for statistical analysis.

Results: No difference was observed between sealed and resealed FS and EX restorations with butt-joint margins. In beveled margins, resealing caused significantly less microleakage ($P<.01$). No differences were found between restorations either sealed or resealed with bevel margins. In butt-joint margins, at the leakage level deeper than 2/3 of the preparation depth, resealed FS showed less microleakage than EX resealed restorations ($P<.01$).

Conclusion: Resealing reduced microleakage in bevel margins, however, in butt-joint margins resealing did not affect the leakage. A significant statistical relationship exists between and within resealing, margin preparation design, type of composite, and microleakage. (Eur J Dent 2012;6:389-395)

Key words: Resin-composite margin design; bevel; butt-joint; surface penetrating sealant; microleakage

■ ¹ Department of Restorative Dentistry, University at Buffalo State University of New York School of Dental Medicine, Buffalo, NY, USA

² Hacettepe University, Faculty of Dentistry, Department of Conservative Dentistry, Ankara, TURKIYE

³ Ankara University, Faculty of Dentistry, Department of Pediatric Dentistry, Ankara, TURKIYE

⁴ Nova Southeastern University, Department of Pediatric Dentistry, Fort Lauderdale, FL, USA

⁵ Nova Southeastern University, Health Professions Division, Fort Lauderdale, FL, USA

■ Corresponding author: Dr. Sibel A. Antonson
University at Buffalo State University of New York, School of Dental Medicine, Department of Restorative Dentistry, 215 Squire Hall, Buffalo, NY, 14214 USA
Tel: +1 716 8292862
Email: sibelat@buffalo.edu

INTRODUCTION

The use of resin composite restorations is increasing due to the benefits derived from adhesive bonding to tooth structure and their esthetic qualities. Despite their wide use, resin composites still present relevant drawbacks such as polymerization shrinkage, which remains a major concern in operative dentistry.¹ Shrinkage stress causes a disruption between the restoration and the preparation wall or a cohesive failure in the restoration or surrounding tooth, which might cause marginal failure of the restoration. Failures may result from marginal leakage that creates the potential for secondary caries, post-operative sensitivity, marginal staining and, if left untreated, advance to pulpal pathology.² The stress generated during polymerization of resin composite is influenced by several factors related to the material, technique, cavity preparation and their respective interactions.³ Therefore, numerous strategies have been proposed such as a layering technique, the use of a flexible lining material or sealing the restoration margins.

Retention and marginal seal might also be improved by beveling enamel margins. Beveling increases favorable end-on etching of enamel prisms and increases the surface area for resin bonding.⁴ Even though there might be advantages, bevels are not usually placed on the occlusal surfaces of posterior teeth or other areas of heavy contact because a conventional preparation design already produces end-on etching of the enamel rods by virtue of the enamel rod direction on occlusal surfaces. Therefore, a beveled preparation design is rarely used for posterior composite restorations.⁴ On the other hand, there are controversial results regarding this issue. In some studies, it has been demonstrated that beveled margins exhibit less microleakage^{5,6} and reduce marginal tooth fracture⁷, while some investigations found no difference between beveled and butt-joint ended margins.^{8,9} It has been proposed that butt-joint margins of well-bonded restorations wear more slowly and create a meniscus appearance against the enamel. However, as beveled composite margins wear, thinner edges of material are produced that are more prone to fracture.¹⁰

The use of surface penetrating sealants is another procedure to improve marginal seal and the longevity of the restorations. These materials have characteristics of wettability and viscosity that can penetrate in the microcracks formed on the surface and to the debonded interface by capillary action.^{11,12} It has been reported that the degree of penetration of the surface sealant and its effectiveness

in increasing the marginal integrity depends on the material's viscosity and the ability to wet the surfaces.^{13,14} Previous studies have shown that surface penetrating sealants were effective in reducing marginal leakage.¹¹⁻¹⁵ However, re-application of sealant might be needed because of the property of this material to wear when exposed to thermal and abrasive oral conditions, consequently losing its effectiveness.

There are advances in resin composite technology that affect their properties, their interaction with dental tissues and marginal integrity. One of the most important discoveries in the last few years is the application of nanotechnology to resin composites. By using nanotechnology, manufacturers can provide highly filled composites with lower shrinkage, higher wear resistance and better polishability and gloss.¹⁶⁻¹⁸ However, new classification of composites may result with different microleakage behavior.

To the extent of the authors' knowledge, no information is available in the literature regarding the relationship of resealing and the design of the preparation margin's effect on microleakage of resin restorations. Therefore, the aim of this *in vitro* study was to evaluate the effect of resealing on microleakage of Class I resin composite restorations in relationship to preparation margin design and resin composite type. The null hypothesis was that the resealing effect on microleakage would not differ according to the margin preparation design and different resin composite type.

MATERIALS AND METHODS

One hundred and twenty eight extracted intact human molar teeth, which had been stored in deionized water with 0.2% sodium azide no longer than one month, was selected for the study. Standardized Class I preparations were completed using a diamond cylinder bur (Diatech, Swiss Dental Instruments, Heerbrugg, Switzerland) in a water-cooled high-speed handpiece. The preparation size was standardized in a mesio-distal direction to a length of 4 mm and a width in the bucco-lingual direction of 2 mm. The depth was set at 2 mm. A new bur was used with every five specimens.

Preparations were then randomly assigned into two groups according to the margin preparation design; half of them were finished with a butt-joint, half of them were beveled with a fine diamond bur (#132F, Brasseler, Savannah, GA, USA). Then the prepared teeth were randomly divided into two groups:

Filtek Supreme (FS): Preparations were etched with 37.5% phosphoric acid (Scotchbond Etchant, 3M ESPE, St Paul, MN, USA) for 30 seconds in enamel and 15 seconds in dentin. After the preparations were thoroughly rinsed with water for 15 seconds, they were air dried gently approximately 10 cm away from the preparation surface for 5 seconds, avoiding complete desiccation. Two consecutive coats of Adper Single Bond (3M Dental Products, St Paul, MN, USA) were applied to the entire preparations, followed by gentle air drying to remove excess solvent, and then light cured with a quartz-tungsten-halogen light (Optilux 501, Kerr, Orange, CA, USA) for 20 seconds. Before use, the curing light was tested with a curing radiometer and found to have an output of at least 475 mW/cm², which was considered adequate. The preparations were then restored with FS in bulk and light-cured with a halogen light for 40 seconds.

Esthet-X (EX): Preparations were etched with 37.5% phosphoric acid (Scotchbond Etchant, 3M ESPE, St Paul, MN, USA) for 30 seconds on enamel and 15 seconds on dentin. After the preparations were thoroughly rinsed with water for 15 seconds, they were gently air dried approximately 10 cm away from the preparation surface for five seconds, avoiding complete desiccation. Prime & Bond NT (Dentsply Caulk, Milford, DE, USA) was applied to thoroughly wet all the tooth surfaces. After the surface remained wet for 20 seconds, excess solvent was removed by gently drying for at least 5 seconds. Prime & Bond NT was cured for 10 seconds using the same curing light. The second coat was applied following the same procedure. The preparations were then restored with EX in bulk and light-cured with a halogen light for 40 seconds.

After 24 hours storage in water at 37°C, all samples were finished with 30-blade carbide burs (#H274UF, Brasseler, Savannah, GA, USA) and polished with abrasive impregnated brushes (Astrobrush, Ivoclar Vivadent, Amherst, NY, USA). The margins of the restorations were etched with 37.5 % phosphoric acid for 15 seconds, subsequently rinsed for 20 seconds with water and air dried for five seconds. A thin coat of surface penetrating sealant, Fortify (Bisco, Schaumburg, IL, USA) was applied and air thinned by blowing a gentle stream of air to ensure an even distribution. Then the surface was polymerized for 10 seconds. The materials used in this study are displayed in Table 1.

After the specimens were stored in distilled water for 24 hours, all specimens were subjected to thermocycling (5,000 cycles at 5°C and 55°C with a 60-second dwell time). They were then treated with a simulated tooth brushing technique using a toothbrush device (V.8 Cross Brushing Machine, Bodine Electric Co., Chicago, IL, USA). The brushing heads were fitted with nylon bristles (Oral B, Procter & Gamble, Cincinnati, Ohio, USA). Care was taken to ensure that bristles were perpendicular to the surface of each sample and touched the surface evenly. A 50:50 (w/w) slurry of toothpaste (Crest, Procter & Gamble) and deionized water was used as abrasive medium. Each surface was brushed 6,000 times using a brush head contact force of 300 grams.

Following the abrasion, the samples were further divided into two sub-groups. While half of each sealant group (n=16/group) was resealed with Fortify, the other half had no treatment. Thermocycling and tooth brushing were repeated for all of the samples following the same protocol described above. After the apices of all root sur-

Table 1. Materials used in this study.

Materials	Composition
Filtek Supreme [3M ESPE St. Paul, MN, USA] Batch #3BF	Filler: Silica/zirconia filler with a mean particle size of 0.6µm Polymeric matrix: Bis-GMA, Bis-EMA, UDMA, TEGDMA
Esthet-X (Dentsply Caulk, Milford, DE, USA) Batch # 0611221	Filler: Barium fluoro alumino borosilicate glass and nano-sized silicon dioxide particles Polymeric matrix: Bis-GMA, TEGDMA, Bis-EMA
Adper Single Bond [3M ESPE St. Paul, MN, USA] Batch # 20051007	Etchant: Scotchbond acid-37% phosphoric acid Bis-GMA, HEMA, co-polymer of acrylic/itaconic acids, diurethane dimethacrylate, glyceroldimethacrylate, water and ethanol
Prime & Bond NT (Dentsply Caulk, Milford, DE, USA) Batch # 0809001941	Di- and Trimethacrylate resins, PENTA, nanofillers-amorphous silicon dioxide, photoinitiators stabilizers, cetylamine hydrofluoride, acetone
Fortify [BISCO, Schaumburg, IL, USA] Batch # G- 9300 F, 0300004571	UDMA, BisEMA
Abbreviations: Bis-GMA: bis-phenol A diglycidylmethacrylate; HEMA: 2-hydroxyethyl methacrylate; UDMA: Urethane dimethacrylate; PENTA: Dipentaerythritol pentacrylate monophosphate; BisEMA: Bisphenol A ethoxylated dimethacrylate; TEGDMA: Triethylene glycol dimethacrylate	

faces were occluded with composite resin, the tooth surfaces were coated with two layers of nail varnish up to 2 mm from the restoration margins. The teeth were immersed in a 5% methylene blue for 8 hours at 37°C and rinsed until all dye was removed from the surface. The specimens were then sectioned through the center of restorations in a mesio-distal direction using a low-speed diamond blade saw (Isomet, Buehler Ltd, Lake Bluff, IL, USA). Some of the samples were unscorable due to the complications during sectioning, and thus eliminated (Table 2). The dye penetration was assessed with three independent calibrated examiners using a light microscope under x40 magnification. Cohen's kappa, calculated to determine inter-and intraexaminer reproducibility was 0.99 and 0.95, respectively. The images were captured by a digital camera connected to computer using image analyzer software.

The dye penetration was scored as follows:

0= no penetration

1= dye penetration up to 1/3 of the restoration depth

2= dye penetration up to 2/3 of the restoration depth,

3= dye penetration to the pulpal wall

A 2x2x2 multi-layered Chi-Square analysis using the Cochran-Mantel-Haenszel test was conducted to see if microleakage was independent of groups ($\alpha=.01$).

RESULTS

The dye penetration scores are displayed in Table 2. Resealing did not cause any significant difference in microleakage scores of FS and EX restorations with butt-joint margins. In bevel margins, resealing caused significantly less microleakage for both of the groups ($P<.01$).

In EX sealed restorations, no difference was found between beveled and butt-joint prepared restorations ($P>.01$). In EX resealed restorations, beveled restorations demonstrated more frequent deep microleakage. While no difference was ob-

served between bevel and butt-joint margins in FS resealed restorations ($P>.01$), margins leaked deeper in beveled restorations in sealed FS restorations ($P<.01$).

When comparing the two resin composites, no statistically significant differences were observed between restorations either sealed or resealed with bevel margins ($P>.01$). In butt-joint margins, resealed FS restorations showed less microleakage than EX resealed restorations at scores 2 ($P<.01$).

A significant statistical relationship exists between and within resealing, margin preparation design, type of composite, and microleakage ($P<.01$).

DISCUSSION

This *in vitro* study evaluated the relationship between the margin preparation design and type of composite on microleakage with or without re-application of surface-penetrating sealant. A number of *in vitro* studies have been conducted that compare the microleakage behavior of beveled and unbeveled restorations. However, the results have not been consistent. In some studies it has been demonstrated that beveled margins exhibit less microleakage than those possessing a standard butt-joint.¹⁹⁻²¹ These studies attributed the results to the increased surface area of the cut enamel caused by beveling, thereby making it more difficult for fluids to penetrate in the restoration-tooth interface. When the enamel margins are beveled to produce transverse sections of enamel prisms, the bond strength between enamel and resin increases.^{22,23} Furthermore, because the beveled region can be firmly bonded to the resin, the enamel margins are reinforced, resulting in an increased resistance of this region to polymerization shrinkage.²⁴

On the other hand, according to Bagheri and Ghavamnasiri²⁵ who compared the marginal leakage of hybrid and microfilled composite resin in Class V restorations with and without an enamel

Table 2. Dye penetration scores.

Score	Bevel				Butt-Joint			
	Filtek Supreme		Esthet-X		Filtek Supreme		Esthet-X	
	Seal	Reseal	Seal	Reseal	Seal	Reseal	Seal	Reseal
0	6	14	7	13	9	11	7	8
1	1	1	1	2	5	4	4	1
2	3	0	5	1	1	1	1	7
3	5	1	2	0	0	0	2	0
Total	15	16	15	16	15	16	14	16

bevel, no significant difference between the two types of composites and two types of enamel margins with respect to microleakage were noted. They reported that an enamel bevel in a Class V preparation had no effect on the reduction of marginal leakage using either hybrid or microfilled composite resin. Similar to this result, Santini et al²⁶ evaluated microleakage around Class V resin-based composite restorations in box-shaped preparations with and without marginal bevels, bonded with self-etch and etch-and-rinse adhesives. They found no significant difference in leakage between beveled and unbeveled groups. Ameri et al²⁷ evaluated the influence of mechanical loading and thermocycling on microleakage of Class V resin-based composite restorations with and without enamel bevels. They found that the non-beveled preparations in this study had significantly less microleakage than the bevel specimens. No benefit was derived from placing an enamel cavosurface bevel on the occlusal margin of standardized Class V composite restorations located at the cementoenamel junction.

In a three year clinical study,²⁸ effects of enamel beveling on the clinical performance of Class V composite restorations was evaluated. At the end of the study, it was claimed that enamel beveling did not significantly affect the clinical performance of restorations. Similar findings were observed in most of the clinical trials.²⁹⁻³² In a meta-analytic study³³ that had assessed the influencing factors on retention loss and marginal discoloration of cervical composite restorations, it was concluded that the additional enamel beveling can be omitted as beveling of the enamel had no significant influence the clinical performance of the restorations.

In the present study, surface penetrating sealant was applied in both types of preparation margin designs, and therefore the results cannot be compared directly with the mentioned previous studies. In the FS resealed restorations, cavity preparation design, bevel vs. butt-joint margins did not affect the leakage scores. However in one-time sealed restorations, beveling caused more leakage in Score 2. On the other hand, no difference was found between bevel and butt-joint margins in EX sealed restorations. However, butt-joint margins showed more leakage in Score 2 in EX resealed restorations. There were no differences between different preparation margin designs in leakage Score of 1. The reason why there was no difference between beveled and butt-joint margins in most of the restorations might be related with the application of surface sealant. In many stud-

ies, surface penetrating sealants were found to be effective in preventing microleakage.¹¹⁻¹⁵

In a clinical study by Dickinson and Leinfelder³⁴ assessing the long-term effect of a surface penetrating sealant, it was observed that surface penetrating sealants not only were effective in reducing wear rates, but also were effective in improving marginal integrity. They also concluded that the surface penetrating sealant's effectiveness could be enhanced if the material was reapplied biannually. Therefore, this current study investigated the effect of resealing on microleakage. Assuming that these sealing agents might lack sufficient abrasion resistance and might be easily lost, the specimens were subjected to tooth brushing simulation. This procedure was repeated after resealing the restorations. After repeating the simulated abrasion, it was found that the sealant should be reapplied for the preparations with a bevel as sealed restorations leaked more than resealed restorations. This finding could be attributed to the thinner edges of material in beveled restorations. As the resin composite margins and surface sealants wear, these areas might become more prone to marginal openings, therefore microleakage. However, re-application of surface sealant did not change the leakage scores in restorations with butt-joint margins. Sealed restorations with butt-joint margins might have been resistant to wear more than restorations with a beveled margin. It has been reported that surface penetrating sealants could also decrease wear on the occlusal surface of posterior resin composite restorations.^{34,35}

Additionally, the relationship between different types of resin composites with different margin design and re-application of sealant was evaluated. Due to the composition of the materials used in this study, it might have been expected that the nanofilled resin composite, FS, might have shown less leakage compared to the microhybrid composite, EX. However the difference between two types of resin composites was only found in butt-joint resealed restorations; where FS restorations showed less leakage in score 2. For the rest of the combinations, both resin composites showed similar leakage scores. This might be due to the similar polymerization shrinkage value of the two resin composites and the similar filler content volume. In previous studies, no significant differences in leakage scores were found between the nanofilled or the microhybrid resin composite materials.³⁶⁻³⁸

As a result of the current study, it can be stated that the resealing effect on microleakage would differ according to the margin preparation de-

sign (bevel or butt-joint) and to the different resin composite type. Therefore, the null hypothesis has to be rejected. Beveled cavity preparations might need frequent resealing procedures in order to avoid microleakage. Although laboratory data provides less reliable evidence than *in vivo* trials, these kinds of microleakage studies can be used as a part of an *in vitro* screening of new techniques or materials. Further clinical studies should be conducted to determine whether the beveling and resealing of restorations would provide any clinical benefit to longevity and reduced marginal staining around restorations.

REFERENCES

1. St Georges AJ, Wilder AD Jr, Perdigão J, Swift EJ Jr. Microleakage of Class V composites using different placement and curing techniques: an in vitro study. *Am J Dent* 2002;15:244-247.
2. Van Meerbeek B, Perdigão J, Lambrechts P, Vanherle G. The clinical performance of adhesives. *J Dent* 1998;26:1-20.
3. Peutzfeldt A, Asmussen E. Determinants of in vitro gap formation of resin composites. *J Dent* 2004;32:109-115.
4. Roberson TM, Heymann HO, Ritter AV. Introduction to composite restorations. In: Roberson TM, Heymann HO, Swift J E (eds). *Sturdevant's Art and Science of Operative Dentistry*. St. Louis: Mosby, 2002:489-490.
5. Eriksen HM, Buonocore MG. Marginal leakage with different composite restorative materials in vitro. Effect of cavity design. *J Oral Rehabil* 1976;3:315-322.
6. Welk DA, Laswell HR. Rationale for designing cavity preparations in light of current knowledge and technology. *Dent Clin North Am* 1976;20:231.
7. Oilo G, Jorgensen KD. Effect of bevelling on the occurrence of fractures in the enamel surrounding composite resin fillings. *J Oral Rehabil* 1977;4:305-309.
8. Eliasson ST, Hill GL. Cavo-surface design and marginal leakage of composite resin restorations. *Oper Dent* 1977;2:55-58.
9. Retief DH, Woods E, Jamison HC. Effect of cavo-surface treatment on marginal leakage in Class V composite resin restorations. *J Prosthet Dent* 1982;47:496-501.
10. Bayne SC, Thompson JY, Taylor DF. Dental Materials. In: Roberson TM, Heymann HO, Swift J EJ (eds). *Sturdevant's Art and Science of Operative Dentistry*. St. Louis: Mosby, 2002:207.
11. dos Santos PH, Pavan S, Assunção WG, Consani S, Correr-Sobrinho L, Sinhorette MA. Influence of surface sealants on microleakage of composite resin restorations. *J Dent Child* 2008;75:24-28.
12. Ramos RP, Chimello DT, Chinelatti MA, Palma Dibb RG, Mondelli J. Effect of three surface sealants on marginal sealing of class V composite resin restorations. *Oper Dent* 2000;25:448-453.
13. Ramos RP, Chinelatti MA, Chimello DT, Dibb RG. Assessing microleakage in resin composite restorations rebonded with a surface sealant and three low-viscosity resin systems. *Quintessence Int* 2002;33:450-456.
14. Reid JS, Saunders WP, Chen YY. The effect of bonding agent and fissure sealant on microleakage of composite resin restorations. *Quintessence Int* 1991;22:295-298.
15. Silva Santana SV, Bombana AC, Flório FM, Basting RT. Effect of surface sealants on marginal microleakage in Class V resin composite restorations. *J Esthet Rest Dent* 2009;21:397-404.
16. Mitra SB, Wu D, Holmes BN. An application of nanotechnology in advanced dental materials. *J Am Dent Assoc* 2003;134:1382-1390.
17. Senawongse P, Pongprueksa P. Surface roughness of nano-fill and nanohybrid resin composites after polishing and brushing. *J Esthet Rest Dent* 2007;19:265-273.
18. Topcu F, Sahinkesen G, Yamanel K, Erdemir U, Oktay EA, Ersahan S. Influence of different drinks on colour stability of dental resin composites. *Eur J Dent* 2009;3:50-56.
19. Schmidlin PR, Wolleb K, Imfeld T, Gygax M, Lussi A. Influence of beveling and ultrasound application on marginal adaptation of box-only Class II (slot) resin composite restorations. *Oper Dent* 2007;32:291-297.
20. Swanson TK, Feigal RJ, Tantbirojn D, Hodges JS. Effect of adhesive systems and bevel on enamel margin integrity in primary and permanent teeth. *Pediatr Dent* 2008;30:134-140.
21. Hall LH, Cochran MA, Swartz ML. Class 5 composite resin restorations: margin configurations and the distance from the CEJ. *Oper Dent* 1993;18:246-250.
22. Crawford PJM, Whittaker DK, Owen GM. The influence of enamel prism orientation on leakage of resin bonded restorations. *J Oral Rehabil* 1987;14:283-289.
23. Munechika T, Suzuki K, Nishiyama M, Ohashi M, Horie K. A comparison of the tensile bond strengths of composite resin to longitudinal and transverse sections of enamel prisms in human teeth. *J Dent Res* 1984;63:1079-1082.
24. Han L, Okamoto A, Iwaku M. The effects of various clinical factors on marginal enamel micro-cracks produced around composite restoration. *Dent Mater J* 1992;11:26-37.
25. Bagheri M, Ghavamnasiri M. Effect of cavo-surface margin configuration of Class V cavity preparations on microleakage of composite resin restorations. *J Contemp Dent Prac* 2008;9:122-129.

26. Santini A, Ivanovic V, Ibbetson R, Milia E. Influence of marginal bevels on microleakage around Class V cavities bonded with seven self-etching agents. *Am J Dent* 2004;17:257-261.
27. Ameri H, Ghavamnasiri M, Abdoli E. Effects of load cycling on the microleakage of beveled and nonbeveled occlusal margins in class V resin-based composite restorations. *J Contemp Dent Pract* 2010;11:25-32.
28. Baratieri LN, Canabarro S, Lopes GC, Ritter AV. Effect of resin viscosity and enamel beveling on the clinical performance of Class V composite restorations: three-year results. *Oper Dent* 2003;28:482-487.
29. Coelho-de-Souza FH, Klein-Júnior CA, Camargo JC, Beskow T, Balestrin MD, Demarco FF. Double-blind randomized clinical trial of posterior composite restorations with or without bevel: 6-month follow-up. *J Contemp Dent Pract* 2010;11:1-8.
30. Perdigão J, Anauate-Netto C, Carmo AR, Lewgoy HR, Cordeiro HJ, Dutra-Corrêa M, Castilhos N, Amore R. Influence of acid etching and enamel beveling on the 6-month clinical performance of a self-etch dentin adhesive. *Compend Contin Educ Dent* 2004;25:33-34.
31. Heintze SD, Ruffieux C, Rousson V. Clinical performance of cervical restorations--a meta-analysis. *Dent Mater* 2010;26:993-1000.
32. Wilson NHF, Wilson MA, Wastell DG, Smith GA. Performance of Occlusion in butt-joint and beveled-edged preparations: Five-year results. *Dent Mater* 1991;7:92-98.
33. Isenberg BP, Leinfelder KF. Efficacy of beveling posterior composite resin preparations. *J Esthet Dent* 1990;2:70-73.
34. Dickinson GL, Leinfelder KF. Assessing the long-term effect of a surface penetrating sealant. *J Am Dent Assoc* 1993;124:68-72.
35. Dickinson GL, Leinfelder KF, Mazer RB, Russell CM. Effect of surface penetrating sealant on wear rate of posterior composite resins. *J Am Dent Assoc* 1990;121:251-255.
36. Hardan LS, Amm EW, Ghayad A, Ghosn C, Khraisat A. Effect of different modes of light curing and resin composites on microleakage of Class II restorations--Part II. *Odontostomatol Trop* 2009;32:29-37.
37. Sadeghi M. Influence of flowable materials on microleakage of nanofilled and hybrid Class II composite restorations with LED and QTH LCUs. *Ind J Dent Res* 2009;20:159-163.
38. Yamazaki PC, Bedran-Russo AK, Pereira PN, Swift EJ Jr. Microleakage evaluation of a new low-shrinkage composite restorative material. *Oper Dent* 2006;31:670-676.