The quality of working impressions for the fabrication of fixed prosthodontics prostheses (crown and bridgework)

Ahmad Syahir Ahmad Zu Saifudin, Fazlieha Kamaruddin, Siti Mariam Ab Ghani

Centre for Restorative Dentistry Studies, Faculty of Dentistry, Universiti Teknologi MARA, 40450 Shah Alam, Selangor, Malaysia

Address for correspondence:

Dr. Siti Mariam Ab Ghani,
Centre for Restorative Dentistry
Studies, Faculty of Dentistry, Universiti
Teknologi MARA, 40450 Shah Alam,
Selangor, Malaysia.
E-mail: sitimariam783@salam.uitm.
edu.my

ABSTRACT

Objective: The study was carried out to assess the quality of working impressions sent to commercial laboratories for fabrication of fixed prostheses. **Materials and Methods:** Impressions (n: 200) received by four dental laboratories were evaluated by two calibrated examiners. The type of work, tray designs, impression materials and techniques were recorded for each impression. Quality data on crucial details of the tooth preparations, voids at tooth preparations, tears along the finished margin line and flow of materials were documented and each criterion scored either with 2 (Good), 1 (Acceptable) or 0 (Unacceptable). The Chi-square test for independence was done for relationship analysis of the impression defects and different type of impression materials. **Results:** From 200 examined impressions, 53.9% were for crown works, 35.9% bridge works, 1.4% posts and cores and 8.8% for other types of work. The impression materials used were polyether (39.5%) and polyvinyl-siloxane (60.5%). The two main types of trays were metal stock (48.5%) and disposable plastic (37.5%). Impression techniques were monophasic one-step technique (50.0%), putty wash two-steps technique (23.5%), putty wash one-step technique (15.5%) and dual phase one-step technique (11.0%). Overall, 64.5% of the impressions sent had unacceptable quality (0 score recorded for at least one criteria). The proportions of impression defects were significant to the type of impression materials ($P < 0.05$). **Conclusion:** The percentage of unacceptable impressions (64.5%) sent to the laboratories is a serious concern, as it contributes to the inaccuracy of the crown and bridgeworks provided to patients.

Key words

Fixed prosthodontics, impressions quality, polyvinyl-siloxane

INTRODUCTION

An impression is defined as a negative likeness or copy in reverse of the surface of an object.^[1] Impression materials in the market can be classified by the chemical type, physical properties, viscosities or by the manufacturers' brand. The widely used classification is according to their elastic properties and chemical type [Figure 1]. Many studies on impression accuracy have been published.^[2-4] Majorities were looking at the resultant dies, which the inaccuracy can also be from factors such as the different techniques for making impressions,^[4] laboratory handling, pouring stage^[5] or the dimensional stability of

the dies. Only few studies reported on the quality of the impressions made clinically.^[6]

The aim of this study was to evaluate the quality of impressions sent to commercial laboratories for fabrication of fixed prosthodontics prostheses, to describe the frequency of clinically detectable impression errors and to determine possible correlations between various factors.

MATERIALS AND METHODS

Four dental laboratories were chosen as the research subject for the reason of good distribution of cases accepted by these laboratories. A total of 200 working impressions for fabrication of fixed prostheses were examined between November 2012 and May 2013 (n: 50 for each laboratory). All of the impressions were evaluated immediately upon reaching the laboratories after collected from various dental clinics to avoid any laboratory handling error. The impressions were also numbered prior to evaluations so that the identities of the

Access this article online	
Quick Response Code:	Website: www.ejgd.org
DOI: 10.4103/2278-9626.134831

Figure 1: Classification of dental impression materials

dentists were unknown to the examiners in preventing bias evaluations. Two calibrated and independent examiners evaluated the impressions. Inter-operator and intra-operator calibration was done in a pilot study between two Year 5 students and a prosthodontist. The prosthodontist was selected as the standard evaluator and Kappa statistical analysis was performed.

For each impression, the type of work, the impression technique, type of tray, retention method of impressions to tray and the material used were recorded. Data on the quality of impressions were documented, including the crucial fine details of the tooth preparation, voids at the tooth preparation, tears at finished margin line and flow of the impression materials (presence of step/streak). Each criterion evaluated was scored either with 2 (Good), 1 (Acceptable) or 0 (Unacceptable).

The collected data were then entered into SPSS version 20 for further analysis. Descriptive result and Chi-square test for independence for relationship analysis of the impression defects and type of impression materials were performed.

RESULTS

From the 200 evaluated impressions, it was identified that 53.9% of the impressions were for crown works, 35.9% for bridge works, 1.4% for posts and cores and 8.8% for other types of prosthodontics works which mainly consist of implant supported fixed prostheses works. The main type of impression materials used by the dental practitioners was polyether (39.5%)

and polyvinyl-siloxane (60.5%). For impression trays, the 2 main types of trays were metal stock trays (48.5%) and disposable plastic trays (37.5%). As for the impression techniques, majority of the dental practitioners made the impressions using monophasic technique (50%), 23.5% putty wash two-steps technique, 15.5% putty wash one-step technique and 11.0% by dual phase one-step technique. The overall results for general evaluation of impressions were shown in Table 1.

The percentage of impressions that were unable to record the fine detail of tooth preparation according to material was PVS addition-cured silicone (37.2%), polyether (28.7%) and PVS condensation cured silicone (28.0%) as shown in Figure 2.

The highest occurrence of unacceptable impression by present of voids at the tooth preparation was polyether (61.2%), PVS condensation-cured silicone (39.2%) and PVS addition-cured silicone (33.8%). The percentage for each material is shown in Figure 3.

For the presence of tears at finished margin line, polyether showed the highest occurrence (32.4%), PVS addition-cured silicone (12.5%) and PVS condensation-cured silicone (12.9%) as shown in Figure 4.

For the presence of flow problem of impression materials, PVS addition-cured silicone showed the highest occurrence (57.4%), polyether (30.5%) and PVS condensation-cured silicone (20.8%). The occurrence of flow problem in each material is shown in Figure 5.

Table 1: General evaluation data for each impression

Type of work		
Crown	117	53.92%
Bridge	78	35.94%
Post and core	3	1.38%
Inlay	0	0.00%
Onlay	0	0.00%
Others-Implant	19	8.76%
Total	217	100.00%
Type of impression material		
Alginate	0	0.00%
Polyether	79	39.50%
Silicone		
Addition	47	23.50%
Condensation (putty)	74	37.00%
Others	0	0.00%
Total	200	100.00%
Type of tray used		
Stock tray		
Disposable plastic tray	75	37.50%
Metal tray	97	48.50%
Others	0	0.00%
Custom-made tray		
Thermoplastic resin	9	4.50%
Light-polimerized acrylic resin	19	9.50%
Others	0	0.00%
Total	200	100.00%
Impression technique		
Putty/Wash technique		
One step	31	15.50%
Two steps	47	23.50%
Dual phase, single step technique	22	11.00%
Monophase, one step technique	100	50.00%
Total	200	100.00%

The status of an overall unacceptable impression was given to any impression that record unacceptable status to any of the four criteria in Table 2. Upon evaluation of the impressions according to the criterion, 64.5% (n: 129/200) of the impressions sent to the four laboratories had unacceptable qualities. The percentage was reported as overall and not specifically according to any laboratories.

Further statistical analysis using Chi-square test of independence was done on each quality criteria and significant relationship was noted ($P < 0.05$) on the proportions of impression defects to the type of impression materials. The quality criteria that were significant were the present of voids, tears at preparation margin and inadequate flow of the impression material.

DISCUSSION

The results of this study indicated that the most commonly used materials by the general practitioners for their crown and bridgeworks were elastomeric

Figure 2: Crucial fine detail of tooth preparation

Figure 3: Voids (air bubbles) at the tooth preparation

Figure 4: Tears at finished margin of tooth preparation

impression material. These practices were concurrent with the practice worldwide. Both polyether and polyvinyl-siloxane impression materials were known to have the ability to record fine details, minimal dimensional change after setting, moderately short working and setting time and excellent recovery from deformation on removal.^[7]

In order to increase the accuracy of working impressions, dimensional stability of an impression tray is also a

contributing factor. Trays should have good stability along a period of time and does not portray any permanent deformation between impression taking and pouring stage.^[5] Metal tray are rigid and will prevent distortion upon usage with high viscosity impression material such as putty^[8] while the custom-made tray will provide uniform space for a uniform polymerization shrinkage of impression material. This study reported that 48.5% uses metal stock trays and only 14% uses custom-made trays for making the working impressions.

There are different impression techniques used with elastomeric impression material with each technique has their advantages and disadvantages. Putty-wash technique was reported that it may eliminate the need of custom-made tray, therefore it coincided with 48.5% of the impressions were taken using metal stock trays in this study. Few researchers believed that the 2-step putty/wash technique is superior as it minimizes the amount of alcohol byproduct, eliminate the polymerization shrinkage from the first impression step (putty) and thereby retains the dimensional stability of the impression.^[3]

The apprehension finding from the present study was that 129 out of 200 impressions (64.5%) were evaluated as unacceptable working impressions. An impression with one criteria in Table 2 scored as unacceptable impression because lacked on one of these criteria can cause major inaccuracy of the fabricated fixed prostheses. The clinicians' identities were not recorded due to ethical issues, although this information could be valuable to determine the impression quality according to the group of clinicians; students, general practitioners or specialists. There are many reasons for the high incidence of unacceptable impressions sent to the laboratories. It could either be clinicians' factors, material properties factors or patient factors. As for clinicians, whether the lack of knowledge and experience, poor manipulation of the impression material, lack of attention to details, low awareness on the need of critical self-evaluation or even financial constraint could be the possible underlying reasons for these unacceptable impressions being sent to the laboratory.

From the histogram [Figures 3 and 4], it can be seen that polyether (monophase) had high incidence of voids and tears in the impressions. This may be explained by the usual improper technique applied by the clinicians

with this material. Technique of just loading the tray without using a small syringe to simultaneously apply material at preparation margins resulted in voids and

Figure 5: Flow problem in impression

Figure 6: Poor detail of tooth preparation

Figure 7: Tear at finished margin

Figure 8: Voids at tooth preparation

Table 2: Criteria for impression quality evaluation

Record crucial fine details of tooth preparations
Voids (air bubbles) at tooth preparation
Tear at finished margin of tooth preparation
Flow of impression material

tears formation. As for flow problems [Figure 5], poor manipulation of PVS addition-cured silicones may cause present of streak and steps in the impression. In dual-phase 1-step technique, unexpected early set of the light-body syringed intra-orally due to oral cavity temperature will form steps with the heavy-body loaded in the tray. Insufficient loading of heavy-body impression into the tray was also the common cause of these errors.

Limitation of the study during the evaluation process was the lack of magnification equipment used during examination as magnification might help to provide better examination of the impressions.

CONCLUSION

The general dental practitioners in Klang Valley areas used reasonable type of trays and impression materials for their crown and bridgework cases. However, within the limitations of this study, we found that the qualities of working impressions sent to the laboratories were unacceptable. The high frequency of detectable errors [Figures 6-8] found in the impressions sent is a serious concern as this will result in poor fitted fixed prostheses provided to patients. A more critical evaluation of impressions by the dentists themselves is recommended. This can be improved by attending short CPD lectures or courses to update their knowledge and skills on current techniques in fixed prosthodontics. These courses may be organized by respected organizations for the general practitioners in the future.

ACKNOWLEDGMENT

We would like to acknowledge all the dental laboratories owners and staffs where we obtained our impressions sample. This study was funded by Research Acculturation Grant Scheme (600-RMI/RAGS 5/3 (126/2012)) grant from Research Management Institute (RMI), Universiti Teknologi MARA.

REFERENCES

1. The glossary of prosthodontic terms. The Academy of Prosthodontics. J Prosthet Dent 1999;71:41-112.
2. Piwowarczyk A, Ottl P, Büchler A, Lauer HC, Hoffmann A. *In vitro* study on the dimensional accuracy of selected materials for monophasic elastic impression making. Int J Prosthodont 2002;15:168-74.
3. Ceyhan JA, Johnson GH, Lepe X. The effect of tray selection, viscosity of impression material, and sequence of pour on the accuracy of dies made from dual-arch impressions. J Prosthet Dent 2003;90:143-9.
4. Joshi PR, Bharat GS, Shrenoy V. Comparative evaluation of dimensional accuracy of addition silicone and condensation silicone. Malays Dent J 2009;30:34-42.
5. Thongthammachai S, Moore BK, Barco MT 2nd, Hovijitra S, Brown DT, Andres CJ. Dimensional accuracy of dental casts: Influence of tray material, impression material, and time. J Prosthodont 2002;11:98-108.
6. Samet N, Shohat M, Livny A, Weiss EI. A clinical evaluation of fixed partial denture impressions. J Prosthet Dent 2005;94:112-7.
7. O'Brien WJ. Dental Materials and their selection. 3rd ed. Quintessence Publishing Co, Inc; 2002. p. 90-112
8. Ghani SM. The accuracy of impressions made using 'Borderlock Mouldable Trays'. Unpublished M Clin Dent dissertation. University of Edinburgh; 2010.

How to cite this article: Zu Saifudin AA, Kamaruddin F, Ab Ghani SM. The quality of working impressions for the fabrication of fixed prosthodontics prostheses (crown and bridgework). Eur J Gen Dent 2014;3:100-4.

Source of Support: Nil, **Conflict of Interest:** None declared.

Announcement

iPhone App

Download
**iPhone, iPad
application**

FREE

A free application to browse and search the journal's content is now available for iPhone/iPad. The application provides "Table of Contents" of the latest issues, which are stored on the device for future offline browsing. Internet connection is required to access the back issues and search facility. The application is Compatible with iPhone, iPod touch, and iPad and Requires iOS 3.1 or later. The application can be downloaded from <http://itunes.apple.com/us/app/medknow-journals/id458064375?ls=1&mt=8>. For suggestions and comments do write back to us.