

Color Stability of Silicone or Acrylic Denture Liners: An in Vitro Investigation

Gulfem Ergun^a, DDS, PhD
Isil Cekic Nagas^b, DDS

ABSTRACT

Objectives: The aim of this study was to compare the color stability of three acrylic based hard liners (Ufi gel hard, Dura-Liner II, Tokuso Rebase) and two silicone based soft liners (Ufi gel permanent, Molloplast B) by using the colorimeter.

Methods: Sixty disc-shaped samples, with uniform size of 10 mm diameter and 2 mm in thickness were fabricated for each material. Thirty samples were made as control group in distilled water and the remaining thirty samples were weathered in accelerated aging chamber. Color measurements were made before and after distilled water and aging. Data were statistically analyzed using nonparametric Kruskal-Wallis and Mann-Whitney U tests.

Results: Data showed that there are significant differences among materials in both after distilled water and aging treatments ($P < .001$). These results indicated that the most discolored liner material was Dura Liner II after aging ($\Delta E^* = 16.30$) and the least discolored material was Ufi gel permanent after distilled water ($\Delta E^* = 0.41$).

Conclusions: Based on the results of this study, silicone based liner materials are considered to be more color stable than acrylic based liner materials. (Eur J Dent 2007;1:144-151)

Key words: Silicone; Acrylic liners; Color stability.

INTRODUCTION

Denture lining materials are widely used for the base of a denture to reduce pain or to improve the fit between the denture and mucous membrane.¹ They act as a cushion and provide an even distribution of functional load onto the stress-bearing mucosa.² Application of a soft lining material to the dentures can also increase the patient's masticatory performance, biting force and improve the chewing rhythm.³

Denture lining materials can be classified

as provisional or permanent, silicone rubber or acrylic resin, and can be either chemically or heat polymerized.⁴ A provisional liner is the one used intraorally for up to 30 days and a long-term liner is categorized as the one that maintains its softness and elasticity for more than 30 days.⁵ Furthermore, in a study, a long term liner was classified to be the one used for 1 year or longer.⁶ Silicone based lining materials are basically dimethylsiloxane polymers and do not contain plasticizer to produce softening effect.⁷ These lining materials are hydrophobic; this reduces water sorption, but simultaneously inhibits good affinity to the supporting tissues.⁸ Acrylic based lining materials are composed of the powder consisting of a higher methacrylate polymer (usually poly ethyl methacrylate) and a liquid of a higher methacrylate monomer (e.g. ethyl, n-butyl), in addition a plasticizer, commonly a phthalate.^{9,10} When im-

^a Associate Professor, Department of Prosthodontics, Faculty of Dentistry, Gazi University, Ankara, Türkiye

^b Research Assistant, Department of Prosthodontics, Faculty of Dentistry, Gazi University, Ankara, Türkiye

■ Corresponding Author: Dr. Gulfem Ergun
Address: Süslü sok. 14/9Tandoğan/Ankara 06580 Türkiye
Tel.: +90 312 213 97 01 Fax: +90 312 223 92 26
E-mail : gulfem@gazi.edu.tr,
ergungulfem@yahoo.com.

mersed in water, these materials undergo 2 processes; leaching of plasticizers and other soluble materials into water and water imbibition by the polymer. Eventually, the physical and mechanical properties of the materials change with time in the patient's mouth.⁹

An ideal processed denture liner should be resistant to imbibing oral fluids or releasing compounds into the saliva. High water sorption and solubility of lining material decrease mechanical properties such as hardness, transverse strength and fatigue limit. Discoloration, dimensional change and separation from a denture base can also appear because of the high values of sorption and solubility parameters.^{3,11} Thus, sorption, solubility and discoloration properties are important to evaluate the longevity of a liner.⁶

Denture relining materials often show changes in mechanical properties with aging.¹² Their longevity was evaluated by immersion in water, accelerated weather testing and thermocycling.¹³⁻¹⁶ The use of accelerated aging process has increased in dental researches recently.¹⁷⁻²⁰ This process simulates the effects of long-term exposure to environmental conditions through an accelerated weathering process that involves ultraviolet light exposure, temperature and humidity changes.²¹ Besides, previous studies have shown the effect of accelerated aging on the physical and mechanical properties of the liner materials.^{12,22}

Color stability is an important property of a denture liner to retain its color in specified environment, especially in long term use. Besides, color assessment and its reproduction is one of the most challenging aspects of dentistry.²³ Visual color matching is still the primary method for evaluating the color and may cause dissatisfying results.^{20,24} Photoelectric tristimulus colorimeters have the potential to remove some of the variables found when the visual method is used exclusively and provide accurate and repeatable measurements.^{25,26}

Color changes in the oral environment need to be investigated further in order to predict which materials will provide the best clinical service in long term use. According to ANSI/ADA Specification No. 12, the denture liner should pass the color stability test, which requires that the specimen show no more than a slight color change after an exposure of 24 hours.²⁷

This requirement might be difficult to achieve because most of the liners show noticeable color changes when exposed to ultraviolet light.²⁸ Hence, the purpose of this in vitro study was to compare the effect of accelerated aging on the color stability of silicone and acrylic denture liners by using a colorimeter.

MATERIALS AND METHODS

Two silicone and three acrylic based lining materials used in this study are listed in Table 1. Sixty disc-shaped samples, with uniform size of 10 mm diameter and 2 mm in thickness, were prepared for each lining material according to the manufacturers' instructions. All of the samples were stored in distilled water (DW) at $37\pm 1^\circ\text{C}$ for 24 hours before color measurement.

Six samples from each tested liner material served as control groups and these samples were immersed in DW at $37\pm 1^\circ\text{C}$ in a dark room for 900 hours. The remaining 6 samples from each group were subjected to accelerated aging in Weather-Ometer instrument (QUV accelerated Weathering Tester, The Q-Panel Company 26200 First St., SN: 92-7475-44, Cleveland, Ohio, USA.) and exposed to continuous ultraviolet and visible-light, at a temperature of 110°F and intermittent DW spray was used for a period of 18 minutes within each 2-hours period. The manufacturer of the weathering instrument estimates that 300 hours of aging intraorally is equivalent to 1 year of clinical service.^{17,29} The samples were kept for 900 hours either in weathering machine or immersed in DW (equal to 3 years of service).

Before and after either aging or immersion in DW, color measurements of the samples were evaluated with the colorimeter (Spectrometer, Gretag Machbeth, SN: KH 1435, Regensdorf, Switzerland). Before each measurement session, the colorimeter was calibrated with its white reference tile according the manufacturer's instructions. The same examiner made three measurements for each sample.

The color change values of all samples were calculated by measuring the mean and standard deviation of ΔE^* values with the use of CIELAB color system.^{20,30} The critical remark of color change (ΔE^*) were quantified by The National Bureau of Standards (NBS) rates the way that a color change is evaluated by the human eye (Table 2). As such,

the color change values of all liner materials were multiplied by a factor of 0.92 to obtain the NBS values.^{22,31}

A Kruskal-Wallis, nonparametric one-way analysis of variance (ANOVA) followed by a multiple comparisons test were used to analyze the k-independent group of data from this investigation. In addition, for two-independent samples comparisons Mann-Whitney U tests were used. All analyses were computed with the SPSS for Windows 11.00 (SPSS Inc., Chicago, IL., USA).

RESULTS

The mean color measurements (L*, a*, and b*) of five liner materials recorded from the colorim-

eter are given in Table 3. The mean and standard deviation of color change (ΔE^*) values and their corresponding NBS values after subjecting them to DW and aging are shown in Table 4. The discoloration occurred after aging was significant when compared to the control samples stored in DW (except UH).

The highest discoloration in all conditions was apparent with DL ($\Delta E^*_{Aging} = 16.30$) (Change to other color) and the least discoloration was found with UP ($\Delta E^*_{DW} = 0.41$) (extremely slight change) after immersion in DW. After aging treatment only DL showed color change to other color (Table 4).

The liner materials were compared with ANOVA and then pairwise comparisons were done by using

Table 1. Properties of the liner materials used in this study.

Material	Code	Type	Composition	Usage Period	Batch No.	Curing Procedure	Manufacturer
Dura-Liner II	DL	Acrylic Based Hard Liner Material Cold curing	P: poly (ethyl methacrylate) L: butylmethacrylate	Permanent	P: 081100 L: 0102300	12 minute at room temperature in teflon mould	Dental Mfg. Co Illinois, USA
Tokuso Rebase	TR	Acrylic Based Hard Liner Material Cold curing	P: poly (ethyl methacrylate) L: α -methacryloyl oxyethyl propionate 1,6-hexanediol dimethacrylate	Permanent	557561E	8 minute at room temperature in teflon mould	Tokuyama Corp. Tokyo, Japan
Ufi Gel Hard	UH	Acrylic Based Hard Liner Material Cold curing	P: poly acrylate L: HEDMA	Permanent	0240.01	7 min at room temperature in teflon mould	Voco, Cuxhaven, Germany
Molloplast B	MP	Silicone Based Soft Liner Material Heat curing	Paste: gama-methacryloxy propyl trimethoxy silan, polydimethyl siloxane	Permanent	020525	15 minute at 200 kg/cm ² pressure in flask, placed in cold water and then heated slowly to 100°C for 2 hours	Detax Ettlingen, Germany
Ufi Gel Permanent	UP	Silicone Based Soft Liner Material Cold curing	B:modified polydimethylsiloxane C: platinum catalyst	Permanent	300.185	12 minute at room temperature in teflon mould	Voco, Cuxhaven, Germany

Kruskal-Wallis nonparametric tests. The results of ANOVA and pairwise comparisons indicated that there were significant differences among the materials after immersion in DW (except UP and DL; MP and TR) (for dw $H=25.455$; $P<.001$) and after aging (except UP and MP) (for aging $H=25.974$; $P<.001$) (Table 5).

The effects of treatments dependent to each material were examined by using Mann-Whitney U tests (Tables 6 and 7). As seen in Table 6, the most discoloring treatment was aging ($\Delta E^*_{DL} = 16.30$, $P=.004$) and the least discoloring treatment was DW ($\Delta E^*_{UP} = 0.41$, $P=.004$). Comparisons between these two treatments showed that there were differences in samples of UP, DL, MP, and TR, but indifferences in samples of UH after immersion in DW and aging.

Control and aging groups were compared based on materials by using two-independent-samples Mann-Whitney U tests (Table 7). Comparisons between these two subgroups showed that there were not differences in samples of acrylic and silicone based liner materials after immersion in DW, but differences in them after aging.

Table 2. NBS rating.

NBS unit	Critical Remarks Of Color Differences
0.0 ~ 0.5	Extremely slight change
0.5 ~ 1.5	Slight change
1.5 ~ 3.0	Perceivable change
3.0 ~ 6.0	Marked change
6.0 ~ 12.0	Extremely marked change
12.0 or more	Change to other color

DISCUSSION

The color instability of the lining materials that may affect the patient's acceptance, have often been reported in clinical studies and may lead to a clinical decision to replace the lining.^{32,33} Even though the properties of lining materials have been much improved, they still have disadvantages including water sorption, solubility and obvious color changes.³⁴ The best liner materials available today do not demonstrate an extended service life of more than a few years.^{6,22}

The technology for dental color matching has changed over the past several decades. In the previous studies, colorimeter measurements have been compared with spectrophotometer readings and deemed as reliable and accurate as spectrophotometer for color difference measurements.^{23,35} The colorimeter used in this study is new, easy to use, portable, offers accurate measurements, the spectral range is 380-730 nm and for illumination it uses D65 gas filled tungsten.

CIELAB color space is commonly used in perceptual studies and dental color assessment because of its uniform coverage of the color space. In this system there are three coordinates: L^* , a^* , b^* . L^* indicates lightness, which ranges from 0 (black) to 100 (white). The quantities a^* and b^* are chromacity coordinates that indicate color directions: positive a^* corresponds to red direction, whereas negative a^* indicates the green direction; positive and negative b^* values correspond to yellow and blue directions, respectively.^{20,35,36} In the present study, a^* values of the tested materials' decreased (to green) either after aging or immersion in DW (except MP after immersion in DW). L^*

Table 3. Color of the liner materials before and after treatments.

Material	Before immersion			After immersion			Before aging			After aging		
	in DW			in DW								
	L^*	a^*	b^*	L^*	a^*	b^*	L^*	a^*	b^*	L^*	a^*	b^*
DL Mean	47.35	15.99	8.00	47.39	15.69	7.93	52.31	16.28	7.93	58.69	7.99	16.50
SD	0.81	0.30	0.26	0.99	0.62	0.27	1.57	0.30	0.27	8.02	3.80	4.69
TR Mean	39.92	20.06	6.24	40.06	19.11	6.40	39.72	24.22	7.15	42.36	12.09	8.07
SD	2.48	1.47	0.49	2.47	1.65	0.63	0.71	0.72	0.45	1.92	1.92	3.25
UH Mean	56.50	9.37	12.25	53.78	9.36	18.47	48.00	12.43	17.66	42.25	12.16	24.05
SD	1.03	0.33	0.70	2.42	0.62	2.18	0.91	0.83	0.39	0.60	0.42	1.75
MP Mean	47.08	12.49	11.68	46.74	13.30	13.02	47.11	13.38	11.38	43.81	11.65	13.92
SD	0.97	0.81	1.41	0.81	0.55	1.11	0.95	0.77	0.60	0.82	0.56	1.42
UP Mean	42.78	17.15	2.94	42.99	17.00	3.16	44.75	16.21	2.89	43.30	15.83	5.75
SD	0.17	0.29	0.18	0.27	0.16	0.16	0.90	0.57	0.85	1.09	0.35	1.16

values of all the tested materials' (except UH and MP) increased (to white) after immersion in DW, while these values (except DL and TR) decreased (to black) after aging. *b** values of the materials' (except DL after immersion in DW) increased (to yellow) both after immersion in DW and aging.

The National Bureau of Standards (NBS) established a rating system to describe color differences by NBS units.²⁰ ΔE^* values of this in vitro study were converted to NBS units to facilitate comparison with clinical studies. According to the NBS units; DL showed change to other color ($\Delta E^*_{DL} = 16.30$), while UP and MP revealed marked change ($\Delta E^*_{UP} = 3.46$, $\Delta E^*_{MP} = 4.78$) after aging. As a result, UP showed the highest color stability after immersion in DW and aging. This property may be of advantage to its long-term serviceability in severe oral cavity environment.

An accelerated aging process has been used in this study in order to simulate the oral environment. Even if the oral environment is more complex, this aging treatment is still useful for the comparison of different lining materials as the closest simulation of oral environment.¹⁷ It has been reported that water spray and visible ultra-

violet light have a direct effect on the properties of liners and cause them to swell.¹⁹ The changes that may occur in polymers as a result of this process are; scission of the polymer chains by UV light, oxygen cross-linking, leaching of plasticizers and absorption of water.³⁷

Previous studies have shown the effectiveness of accelerated aging in evaluating the color stability of soft denture liners.^{17,22} Similarly, in the current study, significant color changes were seen in all of the tested materials after aging.

The clinical color stability behavior or performance of acrylic and silicone based lining materials would be different due to their different structures.³⁸ Water sorption and solubility can dramatically affect stain resistance, dimensional stability, physical and mechanical properties.⁶ When immersed in saliva during clinical use and may be soaked in water or cleansing agents when not in use; plasticizers and other soluble may leach out over extended periods while water is absorbed until equilibrium is reached.¹⁶ At 1 week, water sorption value should not be more than 0.8 mg/cm² and the solubility should not be more than 0.04 mg/cm² for different liners.²⁷ Water sorption

Table 4. Color changes of the liner materials.

Material	Treatment	Mean ΔE^*	SD	NBS unit
DL	Immersion in DW	0.50	0.18	0.46
	Aging	16.30	3.25	14.99
TR	Immersion in DW	1.19	0.70	1.10
	Aging	13.01	1.37	11.96
UH	Immersion in DW	7.13	0.62	6.56
	Aging	8.68	2.12	7.99
MP	Immersion in DW	1.75	1.07	1.61
	Aging	4.78	1.05	4.39
UP	Immersion in DW	0.41	0.11	0.38
	Aging	3.46	1.23	3.18

ΔE^* : Color Change Value SD: Standard Deviation NBS UNIT: National Bureau of Standards Unit

Table 5. Kruskal-Wallis non-parametric test results of the liner materials.

Immersion in DW	Mean ΔE^*	UP	DL	TR	MP	UH
	Mean rank	0.41	0.50	1.19	1.75	7.13
		5.33	8.33	17.00	19.33	27.50
		Kruskal-Wallis H=25.455			P<.001	
Aging	Mean ΔE^*	UP	MP	UH	TR	DL
	Mean rank	3.46	4.78	8.68	13.01	16.30
		4.67	8.50	15.50	22.17	26.67
		Kruskal-Wallis H=25.974			P<.001	

Lines connect values that were not significantly different at the P<.001 level.

depends on the degree of hydrophobicity and porosity of the liner.³ Acrylic resin liners have high water sorption and solubility. On the other hand, silicon liners considered to be stable in aqueous environments for variable lengths of time and the hydrophobicity of them reduces water sorption.^{8,39} These liners might be expected to possess more stain resistant than would the acrylic materials tested. Kawano et al⁶ investigated the sorption and solubility of 12 soft denture liners and reported that MP had sorption values (0.23 ± 0.01) less than 0.8 mg/cm^2 after 1 year and this met the 1 week sorption requirements of ADA specification 12. In the current study, MP had low color change value after immersion in DW ($\Delta E^* = 1.75$) and after aging ($\Delta E^* = 4.78$). This result might be attributed to the low sorption values of MP. Shotwell et al²² investigated the color stability of long term soft liners after accelerated aging and showed the appreciable (marked change) NBS unit of MP (NBS unit, 3.3). Anil et al¹² compared the color stability of five denture relining materials and found the lower NBS unit of MP (NBS unit, 1.94) than TR (NBS unit, 3.8) and UP (NBS unit, 56.05). However, UP was the most color stable liner material in this study (NBS unit, 3.18) and TR showed extremely marked change (NBS unit, 11.96) after aging. The differ-

ences in color measurements of these two studies might be explained by the variations in the properties of the instruments used. This effect should be kept in mind while comparing the results of the researches about the color stability.

In the present study, acrylic and silicone based liners exhibited significantly different color change values after aging. Silicone based liners (UP, MP) seemed to be more resistant to staining than acrylic based liners (UH, TR, DL). Furthermore, comparing acrylic based liners, UH showed marked change than the other acrylic based liners (TR, DL) after immersion in DW. This might lead us to associate this result with the chemical composition of UH, porosity formed by the air inclusions during mixing powder and liquid, surface roughness and water absorption.

Color stability of these materials may vary depending on their monomers' chemical composition.³⁴ Residual monomer is a well-known plasticizer which remains in polymerized resin as free or unreacted monomer and it affects physical and mechanical properties of acrylics.⁴⁰ According to the previous research by Urban et al,^{40,41} comparisons between the residual monomer in hard acrylic relining resins (DL, TR, UH, Kooliner) and heat-polymerized denture base resin (Lucitone

Table 6. Mann-Whitney U test results of the liner materials.

Material	Immersion in DW		Aging		Mann-Whitney U	Significance
	Mean ΔE^*	Mean rank	Mean ΔE^*	Mean rank		
DL	0.50	3.50	16.30	9.50	0.000	P=.004
TR	1.19	3.50	13.01	9.50	0.000	P=.004
UH	7.13	4.50	8.68	8.50	6.000	P=.055
MP	1.75	3.67	4.78	9.33	1.000	P=.006
UP	0.41	3.50	3.46	9.50	0.000	P=.004

n=6, P<.01

Table 7. Mann-Whitney U test results of acrylic and silicone based denture liner materials.

Treatment	Acrylic based liner materials	Silicone based liner materials	Mann-Whitney U	Significance
Immersion in DW (Mean rank)	17.61	12.33	70.000	P=.108
Aging (Mean rank)	21.44	6.58	1.000	P<.001

n=6

550) in 55°C water bath resulted in an arrangement as Kooliner (1.52%) > DL (0.85%) > UH (0.45%) > Lucitone 550 (0.24%) > TR (0.14%). In the present study, DL showed poor color stability after aging ($\Delta E^* = 16.30$). This result might be related to the amount of leaching residual monomer with color stability.

Several studies have been done about the color measurements by using colorimeters^{21,22} and usually these studies have been compared directly. The present results cannot be compared directly with previous studies because of the variations in the instruments used, sample sizes and conditioning of the samples. Although the system of color change is not known exactly, it could be guessed by investigating how aging changes the physical and mechanical properties of denture liners.^{17,19}

Test conditions used for in vitro studies do not subject the materials to the aqueous environment, microorganisms, abrasion, thermocycling, material thickness and cyclic loading. The properties of liner materials in the clinical situations still differ from laboratory testing.⁴² There also seems to be a need for extra researches to understand the effect of aging on color change mechanism.

CONCLUSIONS

■ Accelerated aging affected color stability of all the materials tested.

■ The measurements showed that UP and MP are clinically reliable denture liner materials.

■ From a clinical aspect, for long-term clinical serviceability, it seems reasonable to recommend the use of silicone based instead of acrylic based liner materials.

REFERENCES

1. Fujii K, Arikawa H, Kanie T, Shinohara N, Inoue K. Effect of photo-irradiation on hardness of soft lining materials for denture base. *J Oral Rehabil* 2002;29:744-748.
2. Minami H, Suzuki S, Ohashi H, Kurashige H, Tanaka T. Effect of surface treatment on the bonding of an autopolymerizing soft denture liner to a denture base resin. *Int J Prosthodont* 2004;17:297-301.
3. Hayakawa I, Keh ES, Morizawa M, Muraoka G, Hirano S. A new polyisoprene-based light-curing denture soft lining material. *J Dent* 2003;31:269-274.
4. Garcia RM, Leon BT, Oliveira VB, Del Bel Cury AA. Effect of a denture cleanser on weight, surface roughness and tensile bond strength of two resilient denture liners. *J Prosthet Dent* 2003;89:489-494.
5. Garcia LT, Jones JD. Soft liners. *Dent Clin North Am* 2004;48:709-720.
6. Kawano F, Dootz ER, Koran III A, Craig RG. Sorption and solubility of 12 soft denture liners. *J Prosthet Dent* 1994;72:393-398.
7. Pinto JR, Mesquita MF, Henriques GE, de Arruda Nobilo MA. Effect of thermocycling on bond strength and elasticity of 4 long-term soft denture liners. *J Prosthet Dent* 2002;88:516-521.
8. Walters MGJ, Jagger RG, Polyzois GL. Wettability of silicone rubber maxillofacial prosthetic materials. *J Prosthet Dent* 1999;81:439-443.
9. Polyzois GL, Frangou MJ. Influence of curing method, sealer, and water storage on the hardness of a soft lining material over time. *J Prosthodont* 2001;10:42-45.
10. Haywood J, Basker RM, Watson CJ, Wood DJ. A comparison of three hard chairside denture reline materials. Clinical evaluation. *Eur J Prosthodont Restor Dent* 2003;11:157-163.
11. Parr GR, Rueggeberg FA. In vitro hardness, water sorption, and resin solubility of laboratory-processed and autopolymerized long-term resilient denture liners over one year of water storage. *J Prosthet Dent* 2002;88:139-144.
12. Anil N, Hekimoglu C, Sahin S. The effect of accelerated aging on color stability of denture liners. *J Oral Sci* 1998;3:105-108.
13. Al-Athel M, Jagger R, Jagger D. Effect of ageing on the bond strength of a permanent denture soft lining material. *J Oral Rehabil* 2002;29:992-996.
14. El-Hadary A, Drummond JL. Comparative study of water sorption, solubility, and tensile bond strength of two soft lining materials. *J Prosthet Dent* 2000;83:356-361.
15. Anil N, Hekimoglu C, Buyukbas N, Ercan MT. Microleakage study of various soft denture liners by autoradiography: Effect of accelerated aging. *J Prosthet Dent* 2000; 84:394-399.
16. Leon BL, Del Bel Cury AA, Rodrigues Garcia RC. Water sorption, solubility, and tensile bond strength of resilient denture lining materials polymerized by different methods after thermal cycling. *J Prosthet Dent* 2005;93:282-287.
17. Anil N, Hekimoglu C, Sahin S. Color stability of heat-polymerized and auto-polymerized soft denture liners. *J Prosthet Dent* 1999;81:481-484.
18. Jin C, Nikawa H, Makihira S, Hamada T, Furukawa M, Murata H. Changes in surface roughness and colour stability of soft denture lining materials caused by denture cleansers. *J Oral Rehabil* 2003;30:125-130.
19. Kawano F, Koran A, Nuryanti A, Inoue S. Impact absorption of four processed soft denture liners as influenced by accelerated aging. *Int J Prosthodont* 1997;10:55-60.

20. Ergün G, Mutlu-Sagesen L, Özkan Y, Demirel E. In vitro color stability of provisional crown and bridge restoration materials. *Dent Mater J* 2005;24:342-350.
21. Saygili G, Sahmali S, Demirel F. Color stability of porcelain repair materials with accelerated ageing. *J Oral Rehabil* 2006;33:387-392.
22. Shotwell JL, Razzoog ME, Koran A. Color stability of long-term soft denture liners. *J Prosthet Dent* 1992; 68:836-838.
23. Tung FF, Goldstein GR, Jang S, Hittelman E. The repeatability of an intraoral dental colorimeter. *J Prosthet Dent* 2002;88:585-590.
24. Mutlu-Sagesen L, Ergün G, Özkan Y, Semiz M. Color stability of a dental composite after immersion in various media. *Dent Mater J* 2005;24:382-390.
25. Okubo SR, Kanawati A, Richards MW, Childress S. Evaluation of visual and instrument shade matching. *J Prosthet Dent* 1998;80:642-648.
26. Mutlu-Sagesen L, Ergun G, Özkan Y, Bek B. Color stability of different denture teeth materials: an in vitro study. *J Oral Sci* 2001;43:193-205.
27. ADA American Dental Association Council on Dental Materials and Devices: Specification No. 12: Denture Base Polymers. Chicago, IL, 1975:90.
28. Craig RG, Powers JM. Restorative Dental Materials. 11th ed, St. Louis: Mosby Co, 2002: 667.
29. Douglas RD. Color stability of new-generation indirect resins for prosthodontic application. *J Prosthet Dent* 2000;83:166-170.
30. Cal E, Guneri P, Kose T. Comparison of digital and spectrophotometric measurements of colour shade guides. *J Oral Rehabil* 2006;33:221-228.
31. Korkmaz T, Ergun G, Yılmaz C, Özkan Y. Color stability of glazed and polished dental porcelains. *Int Dent J* 2000;6:333-334.
32. Braden M, Wright PS, Parker S. Soft lining materials-a review. *Eur J Prosthodont Restor Dent* 1995;3:163-174.
33. Polyzois GL, Yannikakis SA, Zissis AJ. Color stability of visible light-cured, hard direct denture reliners: an in vitro investigation. *Int J Prosthodont* 1999;12:140-146.
34. Hayakawa I, Akiba N, Keh E, Kasuga Y. Physical properties of a new denture lining material containing a fluoroalkyl methacrylate polymer. *J Prosthet Dent* 2006; 96:53-58.
35. Analoui M, Papkosta E, Cochran M, Matis B. Designing visually optimal shade guides. *J Prosthet Dent* 2004;92:371-376.
36. Ergün G, Doğan OM, Özkan Y, Demirel E, Doğan A. Color stability of denture base materials after soaked in different aging solutions. *Balk J Stom* 2000;4:93-97.
37. Wagner WC, Kawano F, Dootz ER, Koran A. Dynamic viscoelastic properties of processed soft denture liners: Part I- Initial properties. *J Prosthet Dent* 1995;73:471-477.
38. Hekimoğlu C, Anil N. The effect of accelerated ageing on the mechanical properties of soft denture lining materials. *J Oral Rehabil* 1999;26:745-748.
39. Yoeli Z, Miller V, Zeltser C. Consistency and softness of soft liners. *J Prosthet Dent* 1996;75:412-418.
40. Urban VM, Cass QB, Oliveira RV, Giampaolo ET, Machado AL. Development and application of methods for determination of residual monomer in dental acrylic resins using high performance liquid chromatography. *Biomed Chromatogr* 2006;20:369-376.
41. Urban VM, Machado AL, Oliveira RV, Vergani CE, Pavarina AC, Cass QB. Residual monomer of relines acrylic resins effect of water-bath and microwave post-polymerization treatments. *Dent Mater* 2007;23:363-368.
42. Kiat-Amnuay S, Gettleman L, Mekayarajjananonth T, Khan Z, Goldsmith LJ. The influence of water storage on durometer hardness of 5 soft denture liners over time. *J Prosthodont* 2005;14:19-24.