

Tooth Graft: An Umbrella Overview

Sara Hashemi¹ Shivasadat Tabatabaei² Amirhossein Fathi³ Seyedeh Mohadeseh Asadinejad⁴
Ramin Atash⁵

¹Dental Students Research Committee, School of Dentistry, Isfahan University of Medical Sciences, Isfahan, Iran

²School of Public Health, Boston University, Boston, MA, USA

³Dental Prosthodontics Department, Dental Materials Research Center, School of Dentistry, Isfahan University of Medical Sciences, Isfahan, Iran

⁴Periodontology Department, School of Dentistry, Isfahan University of Medical Sciences, Isfahan, Iran

Address for correspondence Dr. Amirhossein Fathi, DDS, MSc, Department of Prosthodontics, University of Isfahan Hezar-Jarib Ave Isfahan, 81746-73461, Iran (e-mail: amir_alty@yahoo.com).

⁵Department of Prosthodontics, School of Dentistry, Faculty of Medicine, Université Libre de Bruxelles, Brussels, Belgium

Eur J Dent 2024;18:41–54.

Abstract

This umbrella review aims to evaluate systematic/meta-analysis studies containing clinical evidence on tooth grafts as bone substitutes in the oral and maxillofacial regions. Using language restrictions and Preferred Reporting Items for Systematic Reviews and Meta-Analyses (PRISMA) guidelines, an electronic database search of PubMed, MEDLINE, Embase, Cochrane library, and Google Scholar was conducted, featuring published studies up until August 2022. All systematic/meta-analysis review articles relating to tooth graft materials were matched against the inclusion criteria. Two qualified researchers independently assessed the studies' inclusion or exclusion criteria and risk of bias, and a third investigator assisted in resolving ambiguities. A total of 81 systematic/meta-analysis studies, comprising 21 animal-controlled trials, 23 randomized controlled human trials, 23 prospective studies, and 14 retrospective studies, were selected for this study. A small risk of bias was observed in systematic studies/meta-analyses. In addition, the clinical evidence from the analysis of these studies revealed a low incidence of side effects. According to the current review, two systematic reviews indicated that autogenous bone grafting of prepared teeth might be as effective as other bone grafting materials. Four studies also mentioned autologous grafts as potential alternatives to autologous grafts, autogenous demineralized dentin (ADDM), engineered grafts, root blocks, and dental matrix. On the other hand, three systematic studies stated that more long-term research is needed to confirm their findings. Finally, given the importance of standardization and homogeneity of studies for clinical cases, it is advised to be used cautiously due to the risks of transplant rejection.

Keywords

- tooth graft
- bone regeneration
- bone substitutes
- alveolar ridge augmentation

Introduction

Due to the contractile activity of myofibroblasts, the alveolar bone tends to decrease in volume following a tooth extraction, especially on the vestibular side. Therefore, preserving and regenerating alveolar bone has historically been a major challenge in implant dentistry.¹

Dental implants must be firmly stabilized with sufficient bone. Consequently, some patients would be ineligible for implant treatment without horizontal or vertical bone augmentation.² Vertical bone augmentation in the mandible is more challenging and less predictable than horizontal augmentation,² but maxilla sinus management can

provide predictable conditions and satisfactory results for vertical augmentation³.

In the past, bone grafting materials were used to restore the degenerated bone to regenerate alveolar bone due to periodontal diseases, jaw, and facial surgical defects. Increasing advances in dental implantology have led to the development of numerous techniques and procedures, such as bone expansion and sinus floor elevation. Currently, the gold standard for reconstructing hard tissue is an autogenous bone graft.⁴ Nevertheless, donor site issues, virus transmission, resorption, limited access, and the creation of surgical sites can be cited as complications associated with this technique. Due to these factors, numerous studies on bone replacement materials, such as mineralized and freeze-dried bone allografts and synthetic alloplastic grafts, have been conducted.^{5,6}

Using teeth as a graft material has been investigated through case reports and retrospective, prospective studies, randomized controlled trials (RCTs), and controlled clinical trials (CCTs).^{7–12} The general instructions for preparing transplant materials include extraction of autogenous, allogeneic, or xenogeneic teeth, preparation of soft-tissue and tooth fragmentation, demineralization/remineralization, and sterilization. In addition, several animal studies have reported osteoconductive and osteoinductive effects using dentin as an autograft.^{7,13} Some RCTs comparing tooth bone grafts to other bone substitutes found comparable outcomes,^{9,10} while other studies found no difference.¹⁴ In addition, some articles have reported negative side effects, including implant loosening, bone graft failure, and infection.^{11,12}

This umbrella review analyzed nine systematic reviews/meta-analyses (SRs/MAs). Mahardawi et al systematically evaluated oral autogenous bone grafting clinical findings. Their question was: “In partly edentulous individuals, what are the alveolar ridge volume changes, histological findings, and implant durability in locations reinforced using dental autogenous bone grafting?”¹⁵ Li et al compared the clinical and histological efficacy of autogenous demineralized dentin matrix (ADDM) as a bone graft material to Bio-Oss in strengthening oral bone lesions.¹⁶

Bazal-Bonelli et al investigated the clinical effects of autogenous tooth root blocks on ridge reinforcement, implant survival, block absorption, postsurgical complications, and histologic outcomes.¹⁷ Gharpure and Bhatavadekar conducted a comprehensive analysis to compare tooth bone grafts to other bone replacements in the oral and maxillofacial regions.¹⁸ Shavit et al performed a systematic review of sinus augmentation procedures utilizing various tooth-derived bone graft materials and compared the outcomes of dental graft, xenograft, allograft, and alloplastic using radiography and histomorphometry.¹⁹

Starch-Jensen et al conducted a systematic review of the clinical data on implant management after lateral alveolar ridge augmentation (LARA) with autogenous dental block grafting versus autogenous bone block grafting before implant placement.²⁰ Inchigolo et al studied engineered structures, such as tooth block grafts, growth factors, and light modulation applications for bone repair therapy.²¹ Ramanauskaite et al analyzed clinical data regarding the

effect of autogenous teeth on alveolar ridge augmentation.²² Hazballa et al examined the clinical evidence of a tooth as a material for bone augmentation in alveolar ridges.²³

Based on the disparity of results in the literature, this umbrella review aims to evaluate systematic studies with clinical application results of dental bone grafting as a bone substitute in oral and maxillofacial regions.

Method

Study Design

The utilized articles included systematic/meta-analysis reviews and resources examining the outcomes of tooth bone grafts. The methodology adhered to the Cochrane Handbook guidelines, the Preferred Reporting Items for Systematic Reviews and Meta-Analyses (PRISMA) checklist,¹⁸ and several high-quality methodological overviews.^{19,20}

Inclusion Criteria

Study Type

This overview was limited to SRs/MAs of clinical trials, case controls, and cohorts on using tooth substitutes as bone grafting material in craniofacial regions.

Subject Type

Patients who underwent alveolar ridge grafting with a bone substitute were included, regardless of age, race, or gender.

Intervention Types

In the experimental group, the intervention consisted of using a tooth substitute as a grafting material for alveolar ridge/sinus augmentation. In the control group, the intervention comprised autogenous bone blocks, xenogeneic material, allogenic material, or no grafts.

Outcome Measurement Types

The outcome measurements included implant stability; volumetric bone changes; and clinical, histologic, radiologic, immunological, and biochemical evaluation (►Table 1).

In addition, the following criteria were applied to the articles: (1) systematic reviews of at least two primary studies; (2) a focus on the outcomes of using tooth substitutes as bone graft material in human alveolar ridge/sinus augmentation, (3) systematic reviews comprising longitudinal studies examining the impact of use of tooth substitutes for orofacial bone augmentation and reporting at least one type of histological/radiological/clinical outcomes; and (4) publications in English.

We excluded the following: (1) systematic reviews that included only animal studies, (2) systematic reviews that included the use of tooth substitutes for grafting other parts of the human body besides the orofacial region, (3) systematic reviews or meta-analyses with unclear inclusion/exclusion criteria and (4) fully overlapping datasets, and (5) studies that report results other than those of interest.

A search was conducted in the electronic databases PubMed, MEDLINE, EMBASE, Cochrane library, and Google

Table 1 Inclusion and exclusion criteria and outcome evaluation of systematic reviews evaluating tooth graft

Study	Inclusion criteria	Exclusion criteria	Outcome's evaluation
Mahardawi et al ¹⁵	(1) Articles in English, (2) human studies, (3) studies reporting outcomes from six or more autogenous tooth bone graft (ATBG) grafted sites (extraction sockets or ridge defects), (4) studies where ATBG was prepared chairside and (5) was not mixed with another bone graft, and (6) studies with outcomes measured/reported at least 3 mo postoperatively	(1) Studies reporting the success of grafting procedures without quantifiable measurements, (2) publications analyzing aspects irrelevant to the focused question (e.g., probing depths or clinical attachment levels), and (3) studies with an unclear methodology, design, and/or objectives	Alveolar ridge volumetric changes after ridge preservation/augmentation, percentage of new bone formation (from reports on histological findings), marginal bone loss (MBL), implant stability quotient (ISQ), and reported complications or failures related to implants
Inchingolo et al ²¹	<i>In vivo</i> articles on human and animal studies in the field of craniomaxillofacial bone regeneration that highlighted the characteristics of engineered bone constructs and combinations of growth factors and photobiomodulation applications	The exclusion criteria considered for the descriptive analysis were letters to the editor and articles written in non-English languages	Not mentioned
Starch-Jensen et al ²⁰	Studies assessing implant treatment outcome following lateral alveolar ridge augmentation (LARA) with an autogenous tooth (AT) block graft compared with autogenous bone block graft were included by addressing the previously described outcome measures. The review exclusively focused on studies using LARA with an AT block graft and lag-screw fixation prior to implant placement. In addition, at least five patients should be included, and the number of inserted implants and surgical procedures had to be clearly specified	The following exclusion criteria were applied: unspecified length of observation period, insufficient description of the surgical procedure or number of inserted implants as well as studies involving medically compromised patients. Studies assessing the autogenous dentin shell graft technique or particulate AT material in conjunction with delayed or simultaneous placement of implants were excluded as well as letters, editorials, PhD theses, letters to the editor, case reports, abstracts, technical reports, conference proceedings, cadaveric studies, animal or <i>in vitro</i> studies, and literature review papers	<ul style="list-style-type: none"> • Survival of superstructures. This is estimated by subtracting of failed superstructures, which is defined as a complete loss of the superstructure due to technical and/or biological complications • Survival of implants. This is estimated by subtracting of failed implants, which is defined as mobility of previously clinically osseointegrated implants or removal of nonmobile implants due to progressive peri-implant MBL or infection • Implant stability. This is estimated by magnetic resonance frequency analysis, percussion test, or reverse torque test • Health status of the peri-implant tissue (HSPIT). Bleeding on probing, probing depth, mucosal recession, clinical attachment level, and peri-implant marginal bone level as evaluated by clinical and radiographic measurements • Gain in alveolar ridge width. This is estimated by clinical or radiographic measurements • Postoperative dimensional changes of the alveolar ridge width. This is estimated by clinical or radiographic measurements • Patient-reported outcome measures • Biologic and technical complications
Li et al ¹⁶	(1) RCT used for both randomized clinical trial and randomized controlled clinical trial (RCTs); (2) human population; (3) systemic healthy patients who suffered from oral bone defects and needed bone augmentation; (4) bone	(1) Animal trials; (2) reviews, meta-analyses, case reports, retrospective and cohort studies, studies without a comparison group, and conference abstracts and theses; (3) no	The main outcomes including implant stability quotient (ISQ), sinus height (SH), the percentage of new bone formation (NBF) and residual graft material (RGM)

(Continued)

Table 1 (Continued)

Study	Inclusion criteria	Exclusion criteria	Outcome's evaluation
Bazal-Bonell et al ¹⁷	defect sites of patients in the intervention group were grafted using autogenous demineralized dentin matrix (ADDm) or ATBGs; (5) the control group was given Bio-Oss grafts; (6) at least one osteogenic function-related parameter was measured at both the baseline and follow-up time points	outcomes of interest; (4) duplicate studies; and (5) articles with unavailable data	
Hazballa et al ²³	(1) Clinical human studies of alveolar ridge augmentation with autogenous tooth root block (ATRB) grafting; (2) RCTs, cohort studies, case-control studies, cross-sectional studies, and case series; (3) clinical human studies providing the following data: ATRB survival rate, bone gain, bone resorption, implant survival rates, complications, and histological findings; (4) follow-up of at least 6 mo; (5) number of patients/study arm or cohort greater than five patients; (5) articles published in English, Spanish, or German; (6) no restrictions were imposed on publication dates	Exclusion criteria were the following: (1) clinical studies carrying out any other type of ridge augmentation procedure than ATRB grafting; (2) animal studies and case reports; and (3) <i>in vitro</i> studies	The primary outcome analyzed to assess maxillary and mandibular atrophy management was the survival of the ATRB and the survival of implants placed at the augmented sites. Secondary outcomes were intra- and postoperative complications of ATRB and implants, bone gain and resorption in ATRB, changes in marginal bone levels, and histological findings. ATRB survival was considered to be the maintenance of the block in the rehabilitation area, allowing reentry surgery for implant placement. For dental implants, survival was understood as no mobility, no progressive MBL, or infection leading to implant removal
Shavit et al ¹⁹	Study in craniomaxillofacial bone, human study, and publication of the last five	Study in animal, <i>in vivo</i> and <i>ex vivo</i>	Histological outcomes, NBF, and ridge dimension loss
Ramanauskaite et al ²²		<ul style="list-style-type: none"> • Studies in which autogenous tooth was mixed with autogenous bone to graft the maxillary sinus • Studies that evaluated human patients without mentioning their medical condition • Technical notes • Case reports <ul style="list-style-type: none"> • Studies including at least 5 subjects (animal or human) undergoing sinus augmentation. • Studies evaluating the use of tooth-derived graft materials in the sinus augmentation procedure • Studies evaluating the tooth-derived graft material by at least one of the following diagnostic tools: panoramic radiography, computed tomography, histological or histomorphometric analysis • Studies that assessed the tooth-derived graft material by comparing to control groups receiving sinus grafting with other materials such as xenograft, allograft, and alloplast • Follow-up period of at least 4 mo after grafting for human subjects and 8 wk for animals 	<p>Gained bone height after grafting, stability of the sinus graft height, bone formation, and regeneration potential as shown in the histomorphometric analysis, implant stability, complications, and implant survival.</p> <p>NBF (%) RGM (%) Marrow space (%) Osteoid thickness (μm)</p>
		<ul style="list-style-type: none"> • Case reports and studies with unclear designs • Animal studies • Studies assessing the efficacy of interventions aimed at preserving extraction sockets (i.e., procedures aimed at preserving the ridge volume within the envelope existing at the time of extraction) 	<p>Alveolar ridge augmentation Primary outcomes: Alveolar ridge width Cone beam computed tomographic (CBCT) analyses Bone gain at dehiscence-type peri-implant defects</p>

Table 1 (Continued)

Study	Inclusion criteria	Exclusion criteria	Outcome's evaluation
	<ul style="list-style-type: none"> Studies in which lateral ridge augmentation procedures and/or alveolar ridge contour augmentation (i.e., procedures aimed at increasing the ridge volume beyond the skeletal envelope existing at the time of extraction) and/or maxillary sinus floor elevation and/or augmentation of extraction sockets were performed using AT and/or materials other than AT (in controlled studies) at the time of implant placement (simultaneous) or prior to implant placement (staged) AT used as a block or in particulate form with or without additional grafts or barrier membrane Studies reporting on the specified primary or secondary treatment outcome 	<ul style="list-style-type: none"> Studies including patients with compromised systemic health 	<p>Secondary outcomes:</p> <ul style="list-style-type: none"> Postoperative complications Graft resorption Feasibility of implant placement Implant stability Sinus floor elevation Extraction socket augmentation Surgical intraoperative complications Feasibility of implant placement after the healing period
Gharpure and Bhatavadekar ¹⁸	(1) RCT, clinical cohort study, or a well-designed CCT, (2) assessed treatment of tooth bone graft, (3) statistically compared tooth bone graft with ungrafted controls or other graft materials (not applicable for clinical cohort), (4) reported clinical, histologic, radiologic, immunologic, or biochemical results	Studies were excluded if they used additional materials mixed with tooth bone graft. Studies that were not published in peer-reviewed PubMed indexed journals were also excluded	<ul style="list-style-type: none"> Clinical: removal torque value (RTV), ISQ, change in pocket depth, vertical and horizontal dimension of the alveolar bone Histologic: mean new bone formation volume (MNBFV), mean new bone formation area (MNBFBA), trabecular bone area (TBA), new bone formation rate (NBFR), bone implant contact (BIC), crestal width (CW), and augmented area (AA) Radiologic: optical density (OD), bone volume/tissue volume (BV/TV) on CT and micro-CT, bone mineral content (BMC), bone density increase (BDI), mean new bone density (MNBD), vertical and horizontal dimension of the alveolar bone, mean increase in bone height and mean resorption in bone height Immunological: vascular endothelial growth factor (VEGF), angiogenesis percentage (A-P), immunostained osteoblast number (IO-N) labeled for bone morphogenic proteins 2 and 4 (BMP-2 and BMP-4) Biochemical: alkaline phosphatase activity (ALP-A), osteocalcin antigen activity (OC), and microassay for BMP-2, BMP-4, COL1A, RUNX, and CCL2 levels




Fig. 1 Flowchart for the studies identified, screened, and included in the study.

Scholar for articles published up until August 15, 2022, considering language restrictions (only English) and PRISMA guidelines. The search was performed using the Mesh medical subject heading and nonmesh terms in simple or multiple conjunctions. The following keywords were used: (dent*) AND (autogen*) AND ("autogenous tooth bone graft" OR ATBG OR autogen OR tooth graft OR autolog OR ADDM OR allogenous OR xenogenous). These filters were applied to the search results: "systematic review" and "meta-analysis."

Data Extraction

► **Fig. 1** depicts the data extraction procedure utilized in this study. ► **Fig. 2** summarizes the different methods and conditions used for preparation of tooth bone graft material reviewed by SRs/MA.

► **Table 2** details the main characteristics of the studies included. Data extraction from eligible publications was based on systematic/meta-analysis review reports for the tooth bone graft outcomes. Studies were included if they focused on tooth grafting and were in English. Abstracts, review articles, editorial articles, guidelines/protocols, and articles not published with appropriate clinical outcomes were excluded from the study.

Two independent reviewers (M.R. and Q.P.) determined which studies were eligible for analysis (1.0 kappa). One researcher (M.R.) was responsible for extracting qualitative or quantitative data from the studies, while the second researcher (Q.P.) was responsible for validating all qualified information. Information collected included the author's name, the year and type of study, the number of patients, an evaluation of outcomes, a comparison of results, and a conclusion.

Data Analysis

There were significant differences between eligible articles regarding participant inclusion criteria, populations, alternative procedures, and follow-up duration (► **Table 2**), indicating a high degree of heterogeneity among studies. As a result, it is unreasonable to assume that all reviews assessed the same effect.²⁴




Fig. 2 A flow diagram of the different methods of tooth bone graft preparation used is presented.

Table 2 Baseline characteristics of systematic reviews evaluating tooth graft

Study	Types/no. of studies included	No. of patients	Analysis method	Search period	Population	Interventions	Comparison	Main results	Risk of bias	Review quality
Mahardawiet et al ¹⁵	9 RCTs 5 P 6 R	119	SR	Up to May 2021	Patients with alveolar bone defects resulting from tooth extraction/tooth loss who require bone augmentation and implant placement	The use of chairside-prepared autogenous tooth bone graft (ATBG) for bone augmentation and implant placement	The primary outcome was the postoperative volumetric changes in alveolar ridge dimensions, and the secondary outcomes were the implant survival rate at the final follow-up and the percentage of new bone formation in the graft area as determined by harvesting core biopsies	Investigations revealed evidence that autogenous bone grafting using prepared teeth could be as effective as other bone grafting materials	Low	High
Inchingolo et al ²¹	304	-	SR	Up to May 2021	304 articles met the inclusion criteria. Based on the bone substitutes utilized, these articles were divided into allogenic, autologous, xenograft, platelet-derived, laser therapy, microbiota, and mesenchymal cell groups	Explore recent advances in bone repair as they relate to the therapeutic potentials of engineered structures, growth factors, and light modulation applications	Investigate new achievements in bone repair concerning therapeutic potentials based on engineered structures, growth factors, and light modulation applications	Due to the long-term clinical benefit to the oral microbiota and the patient's systemic health, it is possible to use biocompatible and resorbable bone substitutes for bone reconstruction. In addition, growth factors can reduce concurrent diseases of the repair process and enhance the recovery phase following surgery	Low	High
Starch-Jensen et al ²⁰	3 P	65	SR/MA	Up to December 2021	Healthy patients with a horizontal alveolar deficiency following tooth loss, trauma, or congenitally missing tooth/teeth	Lateral alveolar ridge augmentation with an autogenous tooth block graft	Lateral alveolar ridge augmentation with an autogenous bone block graft	A possible alternative to a bone block is the use of a dental block to reinforce the lateral alveolar ridge	Low	High
Li et al ¹⁶	7 RCTs	220	SR/MA	Up to July 2021	Patients with oral bone defects	Autogenous demineralized dentin matrix (ADM) as bone graft material	Bio-Oss	ADDM could be as effective as Bio-Oss in bone augmentation for oral bone defects	Low	High
Bazal-Bonelli et al ¹⁷	5 P 2 R	136	SR	Up to December 2020	Systemically healthy edentulous and partially edentulous patients	A comparison of autogenous tooth root blocks (ATRBs) for alveolar ridge augmentation at dental implant sites	Survival rate and complications of ATRB and implants placed in augmented sites; bone gain and bone resorption of ATRB, and histological results at graft sites	The reconstruction of alveolar crests using ATRBs may be a viable option for single-tooth loss and low levels of bone atrophy in terms of block survival and subsequent implant placement	Low	High
Hazballa et al ²³	3 P 2 Pilot	95	SR	2017–2021	The use of tooth graft in alveolar ridge preservation	An autologous tooth matrix is a bioactive scaffold that		An autologous tooth matrix is a bioactive scaffold that	Low	High

(Continued)

Table 2 (Continued)

Study	Types/no. of studies included	No. of patients	Analysis method	Search period	Population	Interventions	Comparison	Main results	Risk of bias	Review quality
Shavit et al ¹⁹					Human patients with craniomaxillofacial sites defects		Anorganic material, bovine bone, the endodontic treated tooth	paves the way for new developments in bone regeneration. Autologous tooth matrix is a promising material for the preservation of ridges		
Shavit et al ¹⁹	2 P 2 R 3 AC	136	SR	Up to March 2019	Human patients with atrophied posterior maxilla undergoing sinus elevation with bone graft materials produced from teeth	Sinus augmentation using tooth material in different forms: powder, block	Other bone graft materials used in sinus augmentation: allograft, xenograft, and alloplast	Tooth-derived graft materials such as xenograft, allograft, and alloplast could be successful in sinus augmentation procedures	Low	High
Ramanauksaitė et al ²²	3 RCTs 2 P 1R	149	SR	Up to March 2018	Patients exhibiting alveolar ridge deficiencies and needing an implant-retained restoration	Reconstructive procedures employing autogenous teeth (AT) vs. reconstructive procedures employing materials other than AT	Reconstructive procedures employing materials other than AT	AT can be proposed as an alternative material for reconstructing alveolar ridge deficiencies and be effective in the clinic	Low	High
Chapure and Bhatavadekar ¹⁸	4 RCTs 1 R 3 P 18 AC	184	SR	Up to January 2017	Humans with a tooth bone graft in the oral and maxillofacial region	The efficiency of the tooth bone graft used as a bone substitute	Ungrafted sites and/or sites grafted with other bone substitutes, as determined by clinical, histologic, radiologic, immunologic, and biochemical analysis	Tooth bone grafting offers no advantages beyond those of conventional grafting materials. However, nonstandard processing and heterogeneity of study results restrict its clinical application	Low	High

Abbreviations: AC, animal clinical; P, prospective; R, retrospective; RCT, randomized clinical trial; SR/MA, systematic review/meta-analysis.




Fig. 3 The Assessment of Multiple Systematic Reviews 2 (AMSTAR2).

Bias Risk Assessment

We used 16 questions from the Assessment of Multiple Systematic Reviews 2 (AMSR2)²⁵ tool to assess the quality of systematic/meta-analysis review studies based on the risk of bias assessment (►Fig. 3). Each article was ultimately assigned a score that indicates the likelihood of bias in the study. If 8 to 11 questions were answered positively, the risk of bias was low; if 4 to 7 questions were answered positively, the risk of bias was moderate. The risk of bias was deemed high if fewer than three questions received positive responses.²⁶ Two qualified researchers assessed the articles ($\kappa = 0.90$). Inconsistency and ambiguity were resolved through discussions. The third investigator assisted in resolving unresolved issues.

Results

Screening of Systematic/Meta-Analysis Reviews

The PubMed, MEDLINE, EMBASE, Cochrane library, and Google Scholar databases yielded 50 systematic/meta-analysis review articles. After removing duplicate sources, the titles and abstracts of 29 studies remained to be examined. After thoroughly evaluating these publications, 21 met the eligibility criteria, and their full papers were read. Finally, nine review articles^{15–23} were selected for data extraction in the present umbrella study. ►Fig. 1 and ►Table 2 detail the research strategy and summarize the most important characteristics of the articles. Regarding the inclusion and exclusion criteria and evaluation of outcomes, the included SRs exhibited a wide range of approaches (►Table 1). There was

only a slight overlap between the reviews that utilized tooth grafts (►Table 3).

Evidence Quality

AMSR2 was used to evaluate the risk of bias. The level of bias in the study was classified as high, medium, or low based on the number of correct answers (►Fig. 3). The risk of bias in this study (including all systematic and meta-analysis reviews) was low. Clinical evidence consisted of articles with a low risk of bias. To this end, low-risk studies accounted for 100% of the study volume (►Fig. 3).

Characteristics of Systematic Reviews

►Tables 1 and 2 provide general information about each systematic/meta-analysis review. In addition, authors and publication year, number and type of studies, type of analysis, interventions, outcomes, bias risk, key findings, inclusion and exclusion criteria, and outcome evaluation of each SR/MA are reported. ►Fig. 2 summarizes different methods and conditions used for preparation of tooth bone graft material reviewed by SRs/MA.

Mahardawi et al conducted a systematic review that included 20 studies.¹⁵ Li et al systematically searched eight databases for RCT studies. The included studies' quality was assessed using the Cochrane Collaboration's risk tool, and the data were analyzed using Stata 15.0 software.¹⁶ PRISMA guidelines were used in the study of Bazal-Bonelli et al, and the search was conducted in four databases. The Newcastle-Ottawa Quality Assessment Scale¹⁷ was used to assess the quality of the selected studies.

Table 3 Primary included studies included in the systematic reviews for using the tooth material as bone grafting material

Study	Gharpure and Bhattacharya ¹⁸	Shavit et al ¹⁹	Starch-Jensen et al ²⁰	Bazal-Bonelli et al ¹⁷	Mahardawi et al ¹⁵	Li et al ¹⁶	Inchingolo et al ²¹	Ramanauskaite et al ²²	Hazballa et al ²³
Andrade et al ²⁷					x				
Chung and Lee ²⁸	x								
Del Canto-Díaz et al ²⁹				x		x			x
Elfana et al ³⁰				x					
Gomes et al ³¹	x						x		
Jeong et al ³²		x							
Lee et al ³³						x	x		
Jin et al ³⁴				x					
Joshi et al ¹⁰	x								
Jun et al ³⁵	x	x				x	x		
Jung et al ³⁶						x	x		
Kim et al ³⁷			x						
Kim et al ³⁸	x		x						
Kim et al ³⁹			x	x			x		
Kim et al ⁴⁰	x					x	x		
Kim et al ⁴¹			x			x	x		
Lee and Kim ⁴²	x		x						
Li et al ⁴³					x	x			
Melek and El Said ⁴⁴					x	x			
Minamizato et al ⁴⁵					x	x			
Minetti et al ⁴⁶					x	x	x		x
Minetti et al ⁴⁷						x	x		
Minetti et al ⁴⁸						x		x	
Minetti et al ⁴⁹								x	x
Minetti et al ⁵⁰							x		
Movin and Borring-Møller ¹⁴	x							x	
Pang et al ¹⁹	x							x	
Parvini et al ⁵¹							x		
Parvini et al ⁵²							x	x	
Pöhl et al ⁵³							x	x	
Radoczy-Draiko et al ⁵⁴							x		

Table 3 (Continued)

Study	Gharpure and Bhatavadekar ¹⁸	Shavit et al ¹⁹	Starch-Jensen et al ²⁰	Bazal-Bonelli et al ¹⁷	Mahardawi et al ¹⁵	Li et al ¹⁶	Inchingolo et al ²¹	Ramanauskaite et al ²²	Hazballa et al ²³
Sánchez-Labrador et al ⁵⁵									
Santos et al ⁵⁶									
Schwarz et al ⁵⁷									
Schwarz et al ⁵⁸									
Schwarz et al ⁵⁹									
Shejali et al ⁶⁰									
Sohn and Moon ⁶¹									
Valdec et al ⁶²									
Wang et al ⁶³									
Wu et al ⁶⁴									
Xiao et al ⁶⁵									
Xu et al ⁶⁶									
Yüceer-Cetiner et al ⁶⁷									

In the systematic review conducted by Gharpure and Bhatavadekar, a search was conducted to identify animal and human clinical studies and their risk of bias.¹⁸ In the systematic study by Shavit et al, a database search was conducted to identify articles on dental bone grafting in sinus augmentation.¹⁹ In a systematic review by Starch-Jensen et al, searches were conducted in three databases. The Cochrane risk of bias tools, the Newcastle-Ottawa scale, and the GRADE system were utilized to evaluate the quality of included studies.²⁰ In the research conducted by Inchingo et al, four databases were queried.²¹ In the Ramanauskaite et al systematic review, six studies met the criteria for inclusion. Autogenous teeth were utilized in lateral reinforcement, demineralized dentin matrix, vertical reinforcement of sockets after extraction, and height of the lateral sinus floor.²²

In the systematic review by Mahardawi et al, alveolar bone dimensions were reported for heights ranging from -0.64 to +2.26 mm and widths ranging from -1.21 to +0.41 mm. In addition, a significant increase in the dimensions of the additional sites was observed. The survival rate was 98.8% for delayed implant placement and 97.4% for immediate implant placement. Furthermore, utilizing this graft increased the percentage of ossification and bone volume at different time points after surgery.¹⁵

Li et al performed a systematic review of seven RCTs involving 220 patients. These studies observed an insignificant difference in the amount of new bone formation or implant stability. In addition, sinus height and the percentage of residual graft material were significantly lower in patients who received ADDM grafts than in those who received Bio-Oss grafts.¹⁶

In the review by Bazal-Bonelli et al, seven studies involving 136 patients met the inclusion criteria and were examined. Among the patients, 118 were treated with autogenous tooth root blocks (15.99% survival), and 26 were treated with autogenous bone blocks (100% survival). The average bone formation in tooth root blocks was comparable to autologous bone formation. Additionally, the implant survival rate in autogenous tooth root blocks was 98.32%.¹⁷

In the systematic review by Gharpure and Bhatavadekar, the inclusion criteria were met by 18 animal-controlled and 8 human RCTs involving 184 patients. High levels of heterogeneity existed between the selected studies. In more than half of the studies (71.42% of clinical studies and 55.56% of animal studies), tooth and bone grafting did not demonstrate a statistically significant difference between the tooth bone graft and the control group. In addition, 50% of clinical trials and 63.33% of animal studies posed a low risk of bias. Moreover, 350 patients exhibited adverse effects (18.86%).¹⁸

Seven articles met the inclusion criteria for the systematic study by Shavit et al. Data extraction was based on the diagnostic tool type, which included residual alveolar height, increased graft height, and absorption height.¹⁹

In a review conducted by Starch-Jensen et al, three studies met the criteria for inclusion. Comparing these studies revealed no statistically significant differences between the two treatment methods regarding short-term implant

survival, the health of the tissue surrounding the implant, or the occurrence of complications. In contrast, the tooth block resulted in a significantly narrower alveolar ridge than the bone block. However, short-term mucositis was reported more prevalent around dental implants with dental blocks.²⁰

In the survey performed by Inchingolo et al, 304 articles met the criteria for inclusion. Based on the bone substitute utilized, these articles were divided into alloplastic, autologous, xenograft, platelet-derived, laser therapy, microbiota, and mesenchymal cell groups.²¹

Hazballa et al concluded that a dental matrix is a viable option for autologous transplantation because it does not cause an antigenic reaction, permits three-dimensional bone reconstruction, is simple to prepare, and is cost-effective.²³

Discussion

This umbrella review investigates available evidence regarding using tooth substitutes as bone grafting material in the oral and maxillofacial regions. Due to the availability of numerous recent SRs, it became evident that an umbrella review approach should be adopted to avoid duplication of available evidence and to cover all tooth graft techniques comprehensively. This approach was also supported by the fact that most published SRs considered a variety of tooth graft preparation or outcome evaluation techniques. This heterogeneity prevents most of them from conducting a meta-analysis to determine the extent of this graft's effectiveness. In this umbrella review, 9^{15–23} systematic/meta-analysis articles comprising 81 (23 RCTs and 58 non-RCTs) articles were included. The outcomes extracted from these umbrella studies were associated with tooth graft procedures.

All included studies stated that additional long-term research is necessary to confirm their findings. Only one systematic review, which included a meta-analysis, compared the clinical outcomes of demineralized dentin grafts and Bio-Oss and concluded that they are equally effective for augmenting oral bone defects.¹⁶ A systematic review on tooth root blocks concluded that reconstruction of alveolar crests using autogenous tooth root blocks appears to be an adequate solution for single-tooth gaps and low grades of bone atrophy in terms of the survival of the bone block and the implants placed afterward.¹⁷

According to several review articles, the tooth bone graft offers no additional benefits over other graft materials. In addition, the lack of predictability regarding resorption time and clinical success and the lack of standard processing methods restrict the use of this material in clinical practice.¹⁸ Others have demonstrated that the bone formation capacity of autogenous tooth graft is comparable to or greater than that of Bio-Oss or the combination of allograft and xenograft, particularly when used in the maxillary sinus.¹⁹ Following LARA with autogenous tooth block graft, studies indicate a high short-term implant survival and implant stability index. After 26 weeks of functional implant loading, the peri-implant tissue health following LARA with the two treatment modalities was reported to

be comparable. However, a higher incidence of short-term peri-implantitis was observed after LARA with autogenous tooth block grafting.²⁰

The most definitive data for evaluating the osteogenic capability of bone graft material¹⁶ were derived from the histological analysis of human tissue specimens harvested from graft sites. Nevertheless, each study provides a variety of outcome evaluations, such as clinical, radiological, and histological outcomes. Regarding the follow-up duration, SRs did not apply any limitations and the included primary studies showed a variety from 2 weeks to 4 years of follow-up (mostly 6 months). Due to its close proximity to the implant surface,^{68,69} the dental matrix shows promise as a biomaterial for preserving the alveolar ridge. The initial condition of the extracted tooth, its combination with other materials (Bio-Oss, Platelet-rich plasma (PRP), Platelet-Rich-Fibrin (PRF)), the size and shape of the particles (ground, sliced, or in block form), treatment (materials used for demineralization and sterilization), composition (enamel, dentin, cementum, pulp, and soft tissue), and graft dimensions were not standardized among the selected studies.

In addition, except for one study¹⁹ that focused solely on sinus augmentation, other studies did not specify the location of the augmented alveolar bone. Inadequate homogeneity and standardization in the processing of graft material make comparisons with other materials more difficult and diminish the graft material's clinical value. In conclusion, it is evident that the reviewed articles displayed significant heterogeneity and that the original studies are inconclusive and require additional research on this topic. However, given the risks of transplant rejection and the difficulty of obtaining autogenous graft material, tooth grafting can be recommended with caution.

Conclusion and Recommendation

Autogenous tooth bone grafts appear to be effective in oral defect reconstructions compared to Bio-Oss, autogenous bone blocks, or no-grafts, despite the heterogeneity of the included SRs and primary studies, as confirmed by the results of the current umbrella overview. There is some evidence that these techniques improve clinical, histological, or radiological outcomes; however, additional research is needed to inform guideline development and to ensure that treatment recommendations are based on long-term clinical outcomes. There is a clear need to increase the emphasis on using tooth bone grafts in managing alveolar ridge resorption as a mainstream option, as the conventional approaches such as Bio-Oss or autogenous bone blocks are prohibited due to cost or surgical site morbidity.

Conflict of Interest

None declared.

References

- Marconcini S, Denaro M, Cosola S, et al. Myofibroblast gene expression profile after tooth extraction in the rabbit. Materials (Basel) 2019;12(22):3697

- 2 Esposito M, Grusovin MG, Felice P, Karatzopoulos G, Worthington HV, Coulthard P. Interventions for replacing missing teeth: horizontal and vertical bone augmentation techniques for dental implant treatment. *Cochrane Database Syst Rev* 2009;2009(04): CD003607
- 3 Starch-Jensen T, Jensen JD. Maxillary sinus floor augmentation: a review of selected treatment modalities. *J Oral Maxillofac Res* 2017;8(03):e3
- 4 Klijn RJ, Meijer GJ, Bronkhorst EM, Jansen JA. A meta-analysis of histomorphometric results and graft healing time of various biomaterials compared to autologous bone used as sinus floor augmentation material in humans. *Tissue Eng Part B Rev* 2010;16 (05):493–507
- 5 Kolk A, Handschel J, Drescher W, et al. Current trends and future perspectives of bone substitute materials: from space holders to innovative biomaterials. *J Craniomaxillofac Surg* 2012;40(08): 706–718
- 6 Hallman M, Thor A. Bone substitutes and growth factors as an alternative/complement to autogenous bone for grafting in implant dentistry. *Periodontol 2000* 2008;47(01):172–192
- 7 Atiya BK, Shanmuhasuntharam P, Huat S, Abdulrazzak S, Oon H. Liquid nitrogen-treated autogenous dentin as bone substitute: an experimental study in a rabbit model. *J Oral Biol Craniofac Tissue Eng.* 2014;29(02):e165–e170
- 8 Kadkhodazadeh M, Ghasemianpour M, Soltanian N, Sultanian GR, Ahmadpour S, Amid R. Effects of fresh mineralized dentin and cementum on socket healing: a preliminary study in dogs. *J Korean Assoc Oral Maxillofac Surg* 2015;41(03):119–123
- 9 Pang KM, Um IW, Kim YK, Woo JM, Kim SM, Lee JH. Autogenous demineralized dentin matrix from extracted tooth for the augmentation of alveolar bone defect: a prospective randomized clinical trial in comparison with anorganic bovine bone. *Clin Oral Implants Res* 2017;28(07):809–815
- 10 Joshi CP, Dani NH, Khedkar SU. Alveolar ridge preservation using autogenous tooth graft versus beta-tricalcium phosphate alloplast: a randomized, controlled, prospective, clinical pilot study. *J Indian Soc Periodontol* 2016;20(04):429–434
- 11 Jeong K-I, Kim S-G, Kim Y-K, Oh J-S, Jeong M-A, Park J-J. Clinical study of graft materials using autogenous teeth in maxillary sinus augmentation. *Implant Dent* 2011;20(06):471–475
- 12 Park SM, Um IW, Kim YK, Kim KW. Clinical application of auto-tooth bone graft material. *J Korean Assoc Oral Maxillofac Surg* 2012;38(01):2–8
- 13 Catanzaro-Guimarães SA, Catanzaro Guimarães BP, Garcia RB, Alle N. Osteogenic potential of autogenic demineralized dentin implanted in bony defects in dogs. *Int J Oral Maxillofac Surg* 1986;15(02):160–169
- 14 Movin S, Borring-Møller G. Regeneration of infrabony periodontal defects in humans after implantation of allogenic demineralized dentin. *J Clin Periodontol* 1982;9(02):141–147
- 15 Mahardawi B, Rochanavibhata S, Jiaranuchart S, Arunjaroensuk S, Mattheos N, Pimkhaokham A. Autogenous tooth bone graft material prepared chairside and its clinical applications: a systematic review. *Int J Oral Maxillofac Surg* 2023;52(01): 132–141
- 16 Li Y, Zhou W, Li P, Luo Q, Li A, Zhang X. Comparison of the osteogenic effectiveness of an autogenous demineralised dentin matrix and Bio-Oss® in bone augmentation: a systematic review and meta-analysis. *Br J Oral Maxillofac Surg* 2022;60(07): 868–876
- 17 Bazal-Bonelli S, Sánchez-Labrador L, Cortés-Bretón Brinkmann J, et al. Clinical performance of tooth root blocks for alveolar ridge reconstruction. *Int J Oral Maxillofac Implants* 2022;51(05): 680–689
- 18 Gharpure AS, Bhatavadekar NB. Clinical efficacy of tooth-bone graft: a systematic review and risk of bias analysis of randomized control trials and observational studies. *Implant Dent* 2018;27 (01):119–134
- 19 Shavit E, Shavit I, Pinchasov D, Shavit D, Pinchasov G, Juodzbalys G. The Use of tooth derived bone graft materials in sinus augmentation procedures: a systematic review. *J Oral Maxillofac Res* 2019;10(02):e1
- 20 Starch-Jensen T, Vitenson J, Deluiz D, Østergaard KB, Tinoco EMB. Lateral alveolar ridge augmentation with autogenous tooth block graft compared with autogenous bone block graft: a systematic review. *J Oral Maxillofac Res* 2022;13(01):e1
- 21 Inchingolo F, Hazballa D, Inchingolo AD, et al. Innovative concepts and recent breakthrough for engineered graft and constructs for bone regeneration: a literature systematic review. *Materials (Basel)* 2022;15(03):1120
- 22 Ramanauskaite A, Sahin D, Sader R, Becker J, Schwarz F. Efficacy of autogenous teeth for the reconstruction of alveolar ridge deficiencies: a systematic review. *Clin Oral Investig* 2019;23(12): 4263–4287
- 23 Hazballa D, Inchingolo AD, Inchingolo AM, et al. The effectiveness of autologous demineralized tooth graft for the bone ridge preservation: a systematic review of the literature. *J Biol Regul Homeost Agents* 2021;35(2, Suppl. 1):283–294
- 24 Riley RD, Higgins JP, Deeks JJ. Interpretation of random effects meta-analyses. *BMJ* 2011;342:d549
- 25 Shea BJ, Grimshaw JM, Wells GA, et al. Development of AMSTAR: a measurement tool to assess the methodological quality of systematic reviews. *BMC Med Res Methodol* 2007;7(01):10
- 26 Silva V, Grande AJ, Martimbiano ALC, Riera R, Carvalho APV. Overview of systematic reviews - a new type of study: part I: why and for whom? *Sao Paulo Med J* 2012;130(06):398–404
- 27 Andrade C, Camino J, Nally M, Quirynen M, Martínez B, Pinto N. Combining autologous particulate dentin, L-PRF, and fibrinogen to create a matrix for predictable ridge preservation: a pilot clinical study. *Clin Oral Investig* 2020;24(03):1151–1160
- 28 Chung J-H, Lee J-H. Study of bone healing pattern in extraction socket after application of demineralized dentin matrix material. *J Korean Assoc Oral Maxillofac Surg* 2011;37(05):365–374
- 29 Del Canto-Díaz A, de Elío-Oliveros J, Del Canto-Díaz M, Alobera-Gracia M-A, Del Canto-Pingarrón M, Martínez-González J-M. Use of autologous tooth-derived graft material in the post-extraction dental socket. Pilot study. *Med Oral Patol Oral Cir Bucal* 2019;24 (01):e53–e60
- 30 Elfana A, El-Kholy S, Saleh HA, Fawzy El-Sayed K. Alveolar ridge preservation using autogenous whole-tooth versus demineralized dentin grafts: a randomized controlled clinical trial. *Clin Oral Implants Res* 2021;32(05):539–548
- 31 Gomes MF, Abreu PP, Morosolli AR, Araújo MM, Goulart Md. Densitometric analysis of the autogenous demineralized dentin matrix on the dental socket wound healing process in humans. *Braz Oral Res* 2006;20(04):324–330
- 32 Jeong TM, Lee JK. The efficacy of the graft materials after sinus elevation: Retrospective comparative study using panoramic radiography. *Maxillofac Plast Reconstr Surg* 2014;36(04): 146–153
- 33 Lee J-Y, Lee J, Kim Y-K. Comparative analysis of guided bone regeneration using autogenous tooth bone graft material with and without resorbable membrane. *J Dent Sci* 2013;8(03): 281–286
- 34 Jin XY, Kou N, Zhong WJ. Clinical effects of autogenous tooth particles used as bone grafting material in maxillary sinus lift. *Chin J Oral Implantol* 2017;22:174–177
- 35 Jun S-H, Ahn J-S, Lee J-I, Ahn K-J, Yun P-Y, Kim Y-K. A prospective study on the effectiveness of newly developed autogenous tooth bone graft material for sinus bone graft procedure. *J Adv Prosthodont* 2014;6(06):528–538
- 36 Jung G-U, Jeon T-H, Kang M-H, et al. Volumetric, radiographic, and histologic analyses of demineralized dentin matrix combined with recombinant human bone morphogenetic protein-2 for ridge preservation: a prospective randomized controlled trial in comparison with xenograft. *Appl Sci (Basel)* 2018;8(08):1288

- 37 Kim Y-K, Lee J, Um I-W, et al. Tooth-derived bone graft material. *J Korean Assoc Oral Maxillofac Surg* 2013;39(03):103–111
- 38 Kim Y-K, Lee J, Yun J-Y, Yun P-Y, Um I-W. Comparison of autogenous tooth bone graft and synthetic bone graft materials used for bone resorption around implants after crestal approach sinus lifting: a retrospective study. *J Periodontal Implant Sci* 2014;44(05):216–221
- 39 Kim E-S. Autogenous fresh demineralized tooth graft prepared at chairside for dental implant. *Maxillofac Plast Reconstr Surg* 2015;37(01):8
- 40 Kim E-S, Kang J-Y, Kim J-J, Kim K-W, Lee E-Y. Space maintenance in autogenous fresh demineralized tooth blocks with platelet-rich plasma for maxillary sinus bone formation: a prospective study. *Springerplus* 2016;5(01):274
- 41 Kim YK, Pang KM, Yun PY, Leem DH, Um IW. Long-term follow-up of autogenous tooth bone graft blocks with dental implants. *Clin Case Rep* 2017;5(02):108–118
- 42 Lee J-Y, Kim Y-K. Retrospective cohort study of autogenous tooth bone graft. *Oral Biol Res* 2012;36:39–43
- 43 Li P, Zhu H, Huang D. Autogenous DDM versus Bio-Oss granules in GBR for immediate implantation in periodontal postextraction sites: a prospective clinical study. *Clin Implant Dent Relat Res* 2018;20(06):923–928
- 44 Melek LN, El Said MM. Evaluation of “autogenous bioengineered injectable PRF-tooth graft” combination (ABIT) in reconstruction of maxillary alveolar ridge defects: CBCT volumetric analysis. *Saudi Dent J* 2017;8(1–2):86–96
- 45 Minamizato T, Koga T, iT, et al. Clinical application of autogenous partially demineralized dentin matrix prepared immediately after extraction for alveolar bone regeneration in implant dentistry: a pilot study. *Int J Oral Maxillofac Implants* 2018;47(01):125–132
- 46 Minetti E, Palermo A, Ferrante F, et al. Autologous tooth graft after endodontically treated used for socket preservation: a multicenter clinical study. *Appl Sci (Basel)* 2019;9(24):5396
- 47 Minetti E, Palermo A, Contessi M, et al. Autologous tooth graft for maxillary sinus augmentation: a multicenter clinical study. *Int J Growth Factors Stem Cells Dent*. 2019;2(03):45–51
- 48 Minetti E, Berardini M, Trisi P. A new tooth processing apparatus allowing to obtain dentin grafts for bone augmentation: the tooth transformer. *Open Dent J* 2019;13(01):6–14
- 49 Minetti E, Taschieri S, Corbella S. Autologous deciduous tooth-derived material for alveolar ridge preservation: a clinical and histological case report. *Case Rep Dent* 2020;2020:2936878
- 50 Minetti E, Giacometti E, Gambardella U, et al. Alveolar socket preservation with different autologous graft materials: preliminary results of a multicenter pilot study in human. *Materials (Basel)* 2020;13(05):1153
- 51 Parvini P, Sader R, Sahin D, Becker J, Schwarz F. Radiographic outcomes following lateral alveolar ridge augmentation using autogenous tooth roots. *Int J Implant Dent* 2018;4(01):31
- 52 Parvini P, Sahin D, Becker K, Sader R, Becker J, Schwarz F. Short-term outcomes of lateral extraction socket augmentation using autogenous tooth roots: a prospective observational study. *Clin Oral Implants Res* 2020;31(09):881–888
- 53 Pohl S, Binderman I, Tomac J. Maintenance of alveolar ridge dimensions utilizing an extracted tooth dentin particulate autograft and plateletrich fibrin: a retrospective radiographic conebeam computed tomography study. *Materials (Basel)* 2020;13(05):1083
- 54 Radoczy-Drajkó Z, Windisch P, Svidro E, Tajti P, Molnar B, Gerber G. Clinical, radiographical and histological evaluation of alveolar ridge preservation with an autogenous tooth derived particulate graft in EDS class 3–4 defects. *BMC Oral Health* 2021;21(01):63
- 55 Sánchez-Labrador L, Martín-Ares M, Ortega-Aranegui R, López-Quiles J, Martínez-González JM. Autogenous dentin graft in bone defects after lower third molar extraction: A split-mouth clinical trial. *Materials (Basel)* 2020;13(14):3090
- 56 Santos A, Botelho J, Machado V, et al. Autogenous mineralized dentin versus xenograft granules in ridge preservation for delayed implantation in post-extraction sites: a randomized controlled clinical trial with an 18 months follow-up. *Clin Oral Implants Res* 2021;32(08):905–915
- 57 Schwarz F, Hazar D, Becker K, Sader R, Becker J. Efficacy of autogenous tooth roots for lateral alveolar ridge augmentation and staged implant placement. A prospective controlled clinical study. *J Clin Periodontol* 2018;45(08):996–1004
- 58 Schwarz F, Sahin D, Becker K, Sader R, Becker J. Autogenous tooth roots for lateral extraction socket augmentation and staged implant placement. A prospective observational study. *Clin Oral Implants Res* 2019;30(05):439–446
- 59 Schwarz F, Hazar D, Becker K, Parvini P, Sader R, Becker J. Short-term outcomes of staged lateral alveolar ridge augmentation using autogenous tooth roots. A prospective controlled clinical study. *J Clin Periodontol* 2019;46(09):969–976
- 60 Shejali J, Thomas R, Kumar T, Shah R, Mehta DS, Gayathri GV. Immediate ridge augmentation using autogenous tooth root as a block graft in a periodontally hopeless extraction site: a pilot study. *J Oral Implantol* 2020;46(01):41–49
- 61 Sohn D-S, Moon Y-S. Histomorphometric study of rabbit's maxillary sinus augmentation with various graft materials. *Anat Cell Biol* 2018;51(Suppl 1):S1–S12
- 62 Valdec S, Pasic P, Soltermann A, Thoma D, Stadlinger B, Rücker M. Alveolar ridge preservation with autologous particulated dentin—a case series. *Int J Implant Dent* 2017;3(01):12
- 63 Wang W, Jiang Y, Wang D, Mei D, Xu H, Zhao B. Clinical efficacy of autogenous dentin grafts with guided bone regeneration for horizontal ridge augmentation: a prospective observational study. *Int J Oral Maxillofac Implants* 2022;51(06):837–843
- 64 Wu D, Zhou L, Lin J, Chen J, Huang W, Chen Y. Immediate implant placement in anterior teeth with grafting material of autogenous tooth bone vs xenogenic bone. *BMC Oral Health* 2019;19(01):266
- 65 Xiao W, Hu C, Chu C, Man Y. Autogenous dentin shell grafts versus bone shell grafts for alveolar ridge reconstruction: a novel technique with preliminary results of a prospective clinical study. *Int J Periodont Restor Dent* 2019;39(06):885–893
- 66 Xu X, Sohn D-S, Kim H-G, Lee S-J, Moon Y-S. Comparative histomorphometric analysis of maxillary sinus augmentation with deproteinized bovine bone and demineralized particulate human tooth graft: an experimental study in rabbits. *Implant Dent* 2018;27(03):324–331
- 67 Yüceer-Çetiner E, Özkan N, Önger ME. Effect of autogenous dentin graft on new bone formation. *J Craniofac Surg* 2021;32(04):1354–1360
- 68 Schwarz F, Mihatovic I, Golubovic V, Becker J. Dentointegration of a titanium implant: a case report. *Oral Maxillofac Surg* 2013;17(03):235–241
- 69 Minetti E, Carasco A, Carasco M, et al. Il dente come materiale da innesto. Wood Buffalo, AB, Canada: Edra; 2020