

Assessment of consistency in the dimension of gutta-percha cones of ProTaper Next and WaveOne with their corresponding number files

Nitika Bajaj¹, Prashant Monga², Pardeep Mahajan²

Correspondence: Dr. Prashant Monga

Email: artdaentalstudy@yahoo.co.in

¹Department of Pedodontics and Preventive Dentistry, Dasmesh Institute of Research and Dental Science, Faridkot, Punjab, India,

²Department of Conservative Dentistry and Endodontics, Genesis Institute of Dental Sciences and Research, Ferozepur, Punjab, India

ABSTRACT

Objectives: To compare the dimensions of gutta-percha (GP) cones of ProTaper Next (25/0.06) and WaveOne (25/0.08) in relation to their corresponding instruments of the same dimension, respectively. **Materials and Methods:** Two groups of GP cones were made with 25 cones in each group. Group 1 consisted of 25 GP cones # 25/0.06 (ProTaper Next). Group 2 consisted of 25 GP cones # 25/0.08 (WaveOne). Measurements were done at D1 (1 mm short of the tip), D3 (3 mm short of the tip), and D11 (11 mm short of the tip) for GP cones of both groups and were compared with their corresponding instruments. **Results:** Group 1 (ProTaper) 25/0.06 GP points showed greater diameters than those of the corresponding instrument, which was statistically significant. Group 2 (WaveOne) 25/0.08 GP points showed greater diameters than those of the corresponding instrument which was statistically significant whereas it was nonsignificant at level D1. **Conclusion:** Diameters of both ProTaper Next and WaveOne GP cones were greater than their corresponding instruments. Hence, there are chances of under obturation with both systems.

Key words: Gutta-percha, obturation, ProTaper Next, WaveOne

INTRODUCTION

Three-dimensional obturations is one of the main objectives of root canal treatment.^[1] Hence, to achieve this objective, adequate adaptation of gutta-percha (GP) filling to the canal walls is mandatory.^[2]

When GP is used for root canal obturation as solid core material, some minor gaps are commonly left between GP and root canal walls. To fill these gaps and form fluid tight seal, some form of sealer is used. However, these sealers may be a source of microleakage and should be used in minimal amount.^[3] To minimize the

amount of sealer, dimension of master GP cone should closely match the dimension (diameter and taper) of the last instrument used at working length. This compatibility of dimension will lead to adaptation of GP cone to canal wall, thus leaving a minimal space for sealer.^[4] This is particularly important when we are using single file system with corresponding standardized greater taper single GP cone for obturation. For single GP cone obturation technique, standardization of cone is very important.

This is an open access article distributed under the terms of the Creative Commons Attribution-NonCommercial-ShareAlike 3.0 License, which allows others to remix, tweak, and build upon the work non-commercially, as long as the author is credited and the new creations are licensed under the identical terms.

For reprints contact: reprints@medknow.com

How to cite this article: Bajaj N, Monga P, Mahajan P. Assessment of consistency in the dimension of gutta-percha cones of ProTaper Next and WaveOne with their corresponding number files. *Eur J Dent* 2017;11:201-5.

DOI: 10.4103/ejd.ejd_167_16

Access this article online

Quick Response Code:



Website:
www.eurjdent.com

Although in 1958, Ingle and Levine made the first attempt at standardization of GP cones, continuous lack of standardization has been reported in many studies.^[5,6] Variations in tip diameter of master cone from master apical file tip diameter causes difficulty in fitting GP cone at working length, thus causing delay and frustration. These ill-fitting master cones can lead to premature binding or extension of cone beyond apex, thus leading to poor adaptability to canal walls.^[4]

Variations in diameter of GP cones and their corresponding instrument have been studied by various authors.^[7,8] Salles *et al.* in 2013 showed significant differences in diameter of Mtwo system GP cone when compared with their corresponding instrument.^[9]

Hence, in this study, we choose two contemporary single file systems available in market. First is WaveOne nickel-titanium (NiTi) file system from Dentsply Maillefer, Ballaigues, Switzerland, which is a single use, single file system to shape the root canal completely from start to finish. Second is the ProTaper Next system comprising five instruments, but most of the canals can be prepared using only the first two files of this system. Both systems come with GP cones having size corresponding to the last file used at working length.

There is not much literature reporting on the standardization of the dimensions of GP cone of WaveOne and ProTaper Next. Therefore, the present study aimed at comparing the dimensions of GP cones of ProTaper Next (25/0.06) and WaveOne (25/0.08) in relation to their corresponding instruments of the same dimension, respectively.

MATERIALS AND METHODS

A total of fifty GP cones were used for the study. These were divided into two groups of 25 samples each.

Group 1 consisted of 25 GP cones # 25/0.06 (ProTaper Next) each from Lot No. 8222170F.

Group 2 consisted of 25 GP cones # 25/0.08 (WaveOne) each from Lot No. 719915E.

To measure the GP points and instruments, a gauge ruler (Dentsply Maillefer) was used. To match the measuring canal of gauge ruler and metallic millimeter ruler (Camel), both were placed on flat glass slab. There were chances of displacement during

the measurements, so utility wax (Hiflex, Prevest DenPro, India) was used to fix them on glass slab. Measuring site was marked with the aid of fine tip marker pen (Luxor). Diameter measurements at various sites were previously marked at GP cone and instrument was done with the aid of a digital caliper (Precise). Diameter of GP cones of both the groups was compared with their corresponding instruments: X2 ProTaper Next (25/0.06) and WaveOne (25/0.08), respectively.

Measurements were done at D1 (1 mm short of the tip), D3 (3 mm short of the tip), and D11 (11 mm short of the tip) for GP cones of both groups and their corresponding instruments.

Single examiner recorded the readings twice and then those readings were put to statistical analysis.

RESULTS

For fifty GP cones, measurements were done twice by a single examiner for each marked site. Mean of the first and second measurements was put to statistical analysis, and then the standard deviation was obtained. Student's paired *t*-test was applied on the recorded data at 5% level of significance. No statistically significant difference was found between two measurements taken for ProTaper Next GP and WaveOne GP [Tables 1a and b]. The mean and standard deviation of the diameter of GP cones at each site (D1, D3, and D11) were calculated [Tables 2a and b]. Data were further assessed to compare the diameter of GP cones with their corresponding instruments [Tables 3a and b]. Based on the results, it could be concluded that there was variation in the diameter of the GP cones, i.e., they do not correspond to the diameter of corresponding instrument.

Table 1a: Analysis of the reliability of the measurements: Study error (Group 1 - ProTaper Next)

Comparison	n	Mean	SD	Comparison	
				Paired t	P
D1					
First measurement	25	0.3188	0.02651	0.181	0.858
Second measurement		0.3180	0.02291		
D3					
First measurement	25	0.4396	0.02865	0.083	0.934
Second measurement		0.4392	0.01730		
D11					
First measurement	25	0.8804	0.02423	0.976	0.339
Second measurement		0.8752	0.02632		

SD: Standard deviation

In case of ProTaper Next (Group 1) at levels D1, D3, and D11, 25/0.06 GP points showed greater diameters than those of the corresponding instrument, which was statistically significant. However, in case of WaveOne (Group 2) at levels D3 and D11 size, 25/0.08 GP points showed greater diameters than those of the corresponding instrument which was statistically significant whereas it was nonsignificant at level D1.

DISCUSSION

For root canal treatment, rotary NiTi files are preferred over stainless steel files nowadays.^[10] Apart from having an advantage of being flexible, they come in greater taper as compared to 2% taper of stainless steel files. Matching their greater taper, corresponding taper GP cones are available for obturation.^[9] File systems such as WaveOne and ProTaper Next use single file or minimal files for whole canal preparation, thus giving shape to canal similar to the size and taper of their last instrument used at working length. Then, obturation of these canals is done by single GP cone corresponding to size of the last file used for canal preparation. If there is lack of compatibility

between GP cone and the corresponding instrument, obturation will not be adequate. Such inadequate obturation is the main cause for the root canal therapy failure. About 60% of root canal failures occur due to incomplete obturations.^[11] Therefore, the goal of obturation is to provide an impermeable fluid tight seal within the entire root canal system, to prevent oral and apical microleakage.^[1,12] To achieve this goal, size variation between GP cones and instrument should be avoided.

This requires that GP cones used for obturation should be standardized and closely match the last instrument used at working length. Currently, the American and ISO are two organizations which standardize the GP cones.

GP to be used as master cone should have its D1 tip diameter as close as possible to the diameter of instrument at corresponding position as this part of instrument is used for constructing the apical stop.^[13] This size compatibility between the diameter of the GP cone and the instrument will promote a proper fitting of master cone.^[9]

According to the current standards, the accepted diameter of GP cone may vary from 0.005 to 0.007 mm, as followed by most of reputed companies. Such variation means that cone of one stated size can be one size above and/or below, for example, ISO # 25 cone can have ISO # 30 or ISO # 20.

Caliper used for measuring GP cone was placed perpendicular to the points of measurement at each GP cone, so it was possible to measure the greatest diameter.^[13] Due to flexible nature of GP cones and chances of dimensional change with change in temperature, there might be variation in diameter measurement. Further, measuring diameter of

Table 1b: Analysis of the reliability of the measurements: Study error (Group 2 - WaveOne)

Comparison	n	Mean	SD	Comparison	
				Paired t	P
D1					
First measurement	25	0.2852	0.03441	1.072	0.294
Second measurement		0.2944	0.03536		
D3					
First measurement	25	0.4276	0.03166	0.345	0.733
Second measurement		0.4252	0.02293		
D11					
First measurement	25	0.8996	0.02731	0.072	0.943
Second measurement		0.8992	0.02707		

SD: Standard deviation

Table 2a: Descriptive statistical analysis: Gutta-percha cone diameter (Group 1 - ProTaper Next)

Measurement	Size	n	Minimum	Maximum	Mean	SD
D1	25/0.06	25	0.27	0.37	0.3184	0.0222
D3	25/0.06	25	0.41	0.48	0.4394	0.0204
D11	25/0.06	25	0.84	0.92	0.8778	0.0215

SD: Standard deviation

Table 2b: Descriptive statistical analysis: Gutta-percha cone diameter (Group 2 - WaveOne)

Measurement	Size	n	Minimum	Maximum	Mean	SD
D1	25/0.08	25	0.23	0.35	0.2898	0.0275
D3	25/0.08	25	0.40	0.47	0.4264	0.0215
D11	25/0.08	25	0.85	0.94	0.8994	0.0234

SD: Standard deviation

Table 3a: Analysis of the comparison between the diameter of the gutta-percha cones and the instrument (ProTaper Next)

Diameter	Group	n	Mean	SD	P
D1	GP	25	0.3184	0.02216	<0.001
	Instrument	6	0.2483	0.01126	
D3	GP	25	0.4394	0.02038	<0.001
	Instrument	6	0.3692	0.01828	
D11	GP	25	0.8778	0.02151	<0.001
	Instrument	6	0.6392	0.08145	

SD: Standard deviation, GP: Gutta-percha

Table 3b: Analysis of the comparison between the diameter of the gutta-percha cones and the instrument (WaveOne)

Diameter	Group	n	Mean	SD	P
D1	GP	25	0.2898	0.02752	0.818
	Instrument	6	0.2925	0.01255	
D3	GP	25	0.4264	0.02148	<0.001
	Instrument	6	0.4825	0.01754	
D11	GP	25	0.8994	0.02342	<0.001
	Instrument	6	0.7800	0.02168	

SD: Standard deviation, GP: Gutta-percha

these types of materials with metal digital caliper is extremely difficult as slight change in pressure can alter the size. Aguiar *et al.* also used the digital caliper for measurements in their study.^[14]

Experienced endodontist can cope up with diameter and tip size variability while choosing a master cone, but this type of discrepancy can be a nagging problem for inexperienced clinician, resulting in wastage of time. There are also concerns about fit of GP along the entire length of root canal from apical to coronal third as any discrepancy can lead to leakage. These mismatching cones can further result in either over or under obturations, thus causing treatment failure in the long run. In these situations, clinician may either have to cut the tip of GP cones by using GP gauge or use a smaller size GP cones arbitrarily.

However, there is also a concern with the GP gauge that it might not accurately cut larger taper GP cones to the correct tip size because the instrument is designed for use with 0.02 taper cones only.

Kunert *et al.* in 2008 measured adaptation of F1, F2, and F3 GP points at D0 using different gauze rulers.^[15] However, no measuring ruler assessed the adaptation of the GP point and corresponding rotary files adequately. This study presumed that WaveOne or ProTaper Next instruments shaped the

dental walls of root canals to their corresponding shape. However, no consideration was given to the canals shape variations that are frequently present, for example, oval canals. These canal shape variations make it necessary to fill the left out spaces with lateral condensation methods or sealer. Shortcomings of sealers should also have been taken into consideration.

CONCLUSION

In the present study, it was found that the diameters of both the ProTaper Next and WaveOne GP cones were greater than their corresponding instruments. Hence, there are chances of under obturation with both systems. In Group 2, diameter was matching at D1 only, but larger diameter of WaveOne GP cone at D3, D11 can lead to taper lock as well as inadequate adaptation near apical stop. Further research is needed in this area to apply these findings clinically.

Acknowledgments

We would like to thank Genesis Institute of Dental Sciences and Research for allowing and giving ethical clearance to conduct the study.

Financial support and sponsorship

Nil.

Conflicts of interest

There are no conflicts of interest.

REFERENCES

- Schilder H. Filling root canals in three dimensions 1967. *J Endod* 2006;32:281-90.
- Wu MK, van der Sluis LW, Wesselink PR. A preliminary study of the percentage of gutta-percha-filled area in the apical canal filled with vertically compacted warm gutta-percha. *Int Endod J* 2002;35:527-35.
- Desai S, Chandler N. Calcium hydroxide-based root canal sealers: A review. *J Endod* 2009;35:475-80.
- Cunningham KP, Walker MP, Kulild JC, Lask JT. Variability of the diameter and taper of size #30, 0.04 gutta-percha cones. *J Endod* 2006;32:1081-4.
- Hartwell GR, Barbieri SJ, Gerard SE, Gunsolley JC. Evaluation of size variation between endodontic finger spreaders and accessory gutta-percha cones. *J Endod* 1991;17:8-11.
- Zinelis S, Magnissalis EA, Margelos J, Lambrianidis T. Clinical relevance of standardization of endodontic files dimensions according to the ISO 3630-1 specification. *J Endod* 2002;28:367-70.
- Goldberg F, Massone EJ, Pruskin E, Zmerner O. SEM study of surface architecture of gutta-percha cones. *Endod Dent Traumatol* 1991;7:15-8.
- Moule AJ, Kellaway R, Clarkson R, Rowell J, Macfarlane R, Lewis D, *et al.* Variability of master gutta-percha cones. *Aust Endod J* 2002;28:38-43.
- Salles AA, Cord CB, Sonnemann TS, De Melo TA, Irala LE, De Oliveira EP. Comparative analysis of the diameter of MTwo system gutta-percha points in relation to their corresponding instruments. *Rev Sul Brasileira Odontol* 2013;10:49-55.

10. Kim KW, Cho KM, Park SH, Choi KY, Karabucak B, Kim JW. A comparison of dimensional standard of several nickel-titanium rotary files. *Restor Dent Endod* 2014;39:7-11.
11. Saatchi M, Barekatin B, Behzadian M. Comparing the apical microleakage of lateral condensation and chloroform dip techniques with a new obturation method. *Dent Res J (Isfahan)* 2011;8:22-7.
12. Zanoni EM, Leonardo MR, Lia RC, Tagliavini RL. Empty spaces in endodontic fillings. *Rev Gaucha Odontol* 1998;36:232-9.
13. Waechter F, Antunes RO, Irala LE, Limongi O. Comparative evaluation between the diameter of standardized cones and secondary cones B8 calibrated by calibration scale, measuring 1 mm from its tips (D1). *Rev Sul Brasileira Odontol* 2009;6:34-43.
14. Aguiar CM, Cavalcanti JS, Coelho KC. Sealing apical post treatment endodontic. *Rev Gaucha Odontol* 2004;53:281-4.
15. Kunert GK, Melo TA, Oliveira EP, Barletta FB. Accuracy of the tip diameter on gutta-percha cones of different tapers. *Rev Assoc Cir Dent* 2008;62:309-13.